



Designation: D 4570 – 86 (Reapproved 1998)

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Rubber Chemicals—Determination of Particle Size of Sulfur by Sieving (Dry)¹

This standard is issued under the fixed designation D 4570; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

ε¹ NOTE—Section 10 was added editorially in June 1993.

1. Scope

1.1 This test method covers the particle size measurement of the coarse fraction of ground sulfurs. It is limited to measurement of particles greater than 45 μm (No. 325 sieve). If the sulfur is very fine and the screens become plugged by the caking of the sulfur, it may be necessary to use a wet sieve procedure instead.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

E 11 Specification for Wire-Cloth Sieves for Testing Purposes²

E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens²

3. Significance and Use

3.1 This test method is used to evaluate sulfur for suitability as a rubber vulcanizing agent. Sulfur particles must be significantly small enough to dissolve in rubber during cure and produce a uniform network of cross-links. This test method is used as a quality control method to ensure that no excessively large particles are present and to determine if the sulfur follows a typical pattern for size distribution.

4. Apparatus

4.1 *Standard Sieves*, stainless steel, 203 mm in diameter conforming to Specification E 11. The stainless steel cloth shall range in mesh size from 45 to 250 μm. The sieve set should include a lid and a bottom pan.

4.2 *Mechanical Sieve Shakers*, such as a Tyler Ro-Tap³ or equivalent unit.

4.3 *Balance*, with a minimum capacity of 500 g sensitive to 0.1 g.

4.4 *Balance*, with a minimum capacity of 150 g sensitive to 0.001 g.

4.5 *Oven*, circulating air type, controlled to 70 ± 2°C.

5. Reagent

5.1 *Tri-calcium Phosphate*, screened to a fineness of less than 45 μm.

6. Procedure

6.1 Assemble the sieves, each weighed to the nearest 0.1 g, in order of increasing mesh size from bottom to top and add to the bottom pan. Choice of sieves depends on the information desired.

6.2 Weigh into a beaker or suitable container precisely 100.0 g of sulfur. If the sulfur is very fine, add 2.0 g of the fine tri-calcium phosphate (see 5.1) and blend thoroughly using a spatula or glass stirring rod.

6.3 Transfer all the sulfur to the top sieve and add the lid. Fix the sieve vest firmly in the mechanical sieve shaker. Run the unit for 10 min, stop, remove the sieves, and weigh. Return the sieves to the unit and run an additional 3 min. Check the masses of the sieves. Repeat until sieving is complete and the sieves reach constant mass.

7. Calculation

7.1 Determine the residue remaining on each sieve by mass difference. For higher precision, transfer the small residue from the coarser screen to a weighing dish and weigh to the nearest 0.01 g.

7.2 The percent residue on each screen is equal to the amount in grams on each screen.

7.3 The percent residue passing through each screen is determined by accumulating the total percent material collected on that screen and the coarser screens used and subtracting the total from 100.

¹ This test method is under the jurisdiction of ASTM Committee D-11 on Rubber and is the direct responsibility of Subcommittee D11.20 on Compounding Materials and Procedures.

Current edition approved July 8, 1986. Published September 1986.

² *Annual Book of ASTM Standards*, Vol 14.02.

³ This unit may be purchased from the Fisher Scientific Co., 585 Alpha Dr., Pittsburgh, PA 15238.