



Standard Specification for Steel Welded Wire Reinforcement, Plain, for Concrete¹

This standard is issued under the fixed designation A 185; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers welded wire reinforcement to be used for the reinforcement of concrete.

NOTE 1—Welded wire for concrete reinforcement has been described by various terms: welded wire fabric, WWF, fabric, and mesh. The wire reinforcement industry prefers the term “welded wire reinforcement” (WWR) as being more representative of the range of products being manufactured. Therefore, the term “welded wire fabric” has been replaced with the term “welded wire reinforcement” in this specification and in related specifications.

1.2 The values stated in inch-pound or SI units are to be regarded as standard. Within the text the inch-pound units are shown in parenthesis. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:

A 82 Specification for Steel Wire, Plain, for Concrete Reinforcement²

A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment³

2.2 Military Standards:

MIL-STD-129 Marking for Shipment and Storage⁴

MIL-STD-163 Steel Mill Products Preparation for Shipment and Storage⁴

2.3 Federal Standard:

Fed. Std. No. 123 Marking for Shipments (Civil Agencies)⁴

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Sept 10, 2002. Published June 2003. Originally published as A 185 – 36 T. Last previous edition A 185 – 01.

² Annual Book of ASTM Standards, Vol 01.04.

³ Annual Book of ASTM Standards, Vol 01.05.

⁴ Available from Standardization Documents, Order Desk, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

3.1.1 *convoluted wire*—when wire for welded wire reinforcement is formed into a sinusoidal wave shape, it is commonly referred to as convoluted wire. The wire is used in the manufacture of cages for certain applications of concrete pipe reinforcing.

3.1.2 *welded wire reinforcement—as used within the scope and intent of this specification*, designates a material composed of cold-drawn steel wire, as-drawn or galvanized, fabricated into sheets or rolls by the process of electric resistance welding. The finished material shall consist essentially of a series of longitudinal and transverse wires arranged substantially at right angles to each other, and welded together at points of intersection.

4. Ordering Information

4.1 Orders for material to this specification should include the following information:

4.1.1 Quantity (weight or square area),

4.1.2 Name of material (welded wire reinforcement for concrete),

4.1.3 Wire spacings and sizes,

4.1.4 Minimum yield strength if Supplement S 1 of Specification A 82 applies.

4.1.5 Exclusion of oversteeling, if required (see 8.4.2),

4.1.6 Length and width of sheets or rolls,

4.1.7 Packaging (see Section 16), and

4.1.8 ASTM designation and year of issue.

NOTE 2—A typical ordering description is as follows: 10 000 ft² welded wire reinforcement for concrete, 4 × 12-W15 × W 6, in flat sheets 96 in. wide by 240 in. long, in secured lifts, to ASTM A 185—_____.

5. Materials

5.1 The wire used in the manufacture of welded wire reinforcement shall conform to Specification A 82 and its Supplement S1 if so ordered.

5.2 Welded wire reinforcement shall be furnished either in flat sheets, or in rolls, as specified by the purchaser.

*A Summary of Changes section appears at the end of this standard.