



Standard Specification for Steel Forgings, Carbon and Alloy, for Pinions, Gears and Shafts for Reduction Gears¹

This standard is issued under the fixed designation A 291; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers normalized and tempered carbon steel and quenched and tempered alloy steel forgings for pinions, gears, and shafts.

1.2 Several grades of steel are covered as follows:

1.2.1 *Grade 1 Class A* is normalized and tempered carbon steel.

1.2.2 *Grade 2 Class B, Grade 3 Class C, Grade 3A Class D, Grades 4 to 7 Classes E, F, G, and H, Grade 8 Class I, and Grade 9 Class J* are liquid quenched and tempered alloy steel.

1.3 All grades and classes are considered weldable under proper conditions. Welding technique is of fundamental importance and it is presupposed that welding procedure and inspection shall be in accordance with approved methods for the class of material used.

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

A 275/A 275M Test Method for Magnetic Particle Examination of Steel Forgings²

A 388/A 388M Practice for Ultrasonic Examination of Heavy Steel Forgings²

A 788 Specification for Steel Forgings, General Requirements²

3. Ordering Information

3.1 Instructions for purchasing forgings to this specification should be in accordance with Specification A 788. In addition, a detailed drawing, sketch, or written description of the forging should be included with the inquiry or order.

3.2 Supplementary requirements are provided and shall apply only when specified in the purchase order.

4. Heat Treatment

4.1 Preliminary Heat Treatment:

4.1.1 The forgings shall be given such preliminary heat treatment as is proper for the design and composition. The forgings shall be heated to a suitable temperature for a sufficient length of time for austenitization and shall be suitably cooled to bring about complete transformation.

4.1.2 Forgings may be immediately treated for mechanical properties after preliminary heat treatment or may be rough turned prior to treatment for mechanical properties.

4.2 *Heat Treatment for Mechanical Properties*—The forging shall be reheated to a temperature above the upper critical temperature and held a sufficient length of time for complete austenitization. Grade 1 shall be air cooled while Grades 2 through 9 shall be liquid quenched.

4.3 *Tempering*—The forgings shall be tempered to develop the specified properties. Minimum tempering temperatures shall be as follows:

Grade	Class	Minimum Tempering Temperature	
		°F	(°C)
1 and 2	A and B	1150	(620)
3, 3A, and 4	C, D, and E	1075	(580)
5, 6, 7	F, G, and H	1050	(565)
8	I	1100	(595)
9	J	1000	(540)

The charge shall be cooled under uniform conditions in the furnace at a maximum rate of 100°F (55°C) per h to 600°F (316°C).

4.4 *Stress Relief*—If the manufacturer elects to heat treat for mechanical properties prior to machining, the forgings shall be stress relieved after machining (4.5) at a temperature that is 50 to 100°F (28 to 55°C) below the last previous tempering temperature but in no case below 1000°F (540°C). The forgings shall be cooled under uniform conditions in the furnace at a maximum rate of 100°F (55°C)/h to 600°F (316°C).

4.5 Machining:

4.5.1 Rough machining before heat treatment for mechanical properties may be performed at the option of the manufacturer.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved Apr. 10, 2003. Published June 2003. Originally approved in 1946. Last previous edition approved in 2002 as A291 – 02.

² *Annual Book of ASTM Standards*, Vol 01.05.

*A Summary of Changes section appears at the end of this standard.