



Designation: A 496 – 97a<sup>ε1</sup>

## Standard Specification for Steel Wire, Deformed, for Concrete Reinforcement<sup>1</sup>

This standard is issued under the fixed designation A 496; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

<sup>ε1</sup> NOTE—Editorial changes were made throughout in June 2001.

### 1. Scope

1.1 This specification covers deformed steel wire which has been cold-worked by drawing, rolling, or both drawing and rolling, to be used as produced, or in fabricated form, for the reinforcement of concrete in sizes having nominal cross-sectional areas not less than 6.45 mm<sup>2</sup> (0.01 in.<sup>2</sup>).

1.2 Supplement S1 describes high-strength wire, which shall be furnished when specifically ordered. It shall be permissible to furnish high-strength wire in place of regular wire if mutually agreed to by the purchaser and supplier.

1.3 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text the inch-pound units are shown in brackets. The value stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values may result in nonconformance with the specification.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products<sup>2</sup>

A 497 Specification for Steel Welded Wire Fabric, Deformed, for Concrete Reinforcement<sup>3</sup>

A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment<sup>4</sup>

E 83 Practice for Verification and Classification of Extensometers<sup>5</sup>

#### 2.2 Military Standards:

MIL-STD-129 Marking for Shipment and Storage<sup>6</sup>

MIL-STD-163 Steel Mill Products Preparation for Shipment and Storage<sup>6</sup>

#### 2.3 Federal Standard:

Fed. Std. No. 123 Marking for Shipments (Civil Agencies)<sup>6</sup>

#### 2.4 Other Standard:

ACI 318 Building Code Requirements for Structural Concrete<sup>7</sup>

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *deformed steel wire for reinforcement*—as used within the scope and intent of this specification, shall mean any cold-worked, deformed steel wire intended for use as reinforcement in concrete construction, the wire surface having deformations that: (1) inhibit longitudinal movement of the wire in such construction; and (2) conform to the provisions of Section 5. It shall be permissible for the deformations to be raised indented.

3.1.2 *size number*—as used in this specification, refers to the numerical designation of the wire as tabulated in Table 1 and Table 2 under the column headed Deformed Wire Size Number, or a number indicating the nominal cross-sectional area of the deformed wire in hundredths of a square inch.

### 4. Ordering Information

4.1 When deformed wire is ordered by size number, the dimensional requirements shall be as given in Table 1. When deformed wire is ordered to dimensions other than the sizes shown, the nominal dimensions shall be developed from the applicable unit weight per foot of the section.

4.2 Orders for material to this specification should include the following information:

4.2.1 Quantity (weight),

4.2.2 Name of material (deformed steel wire for concrete reinforcement),

4.2.3 Wire diameter (see Table 1 and Table 2),

4.2.4 Packaging (see Section 16), and

4.2.5 ASTM designation and year of issue.

4.2.6 Special requirements, if any. (See Supplement S1.)

NOTE 1—A typical ordering description is as follows: 50 000 lb deformed steel wire for concrete reinforcement, size No. D-12, on pipe carriers, polyethylene shrouded, the ASTM A 496 — \_\_\_\_ .

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Dec. 10, 1997. Published December 1998. Originally published as A 496 – 64. Last previous edition A 496 – 97.

<sup>2</sup> Annual Book of ASTM Standards, Vol 01.03

<sup>3</sup> Annual Book of ASTM Standards, Vol 01.04

<sup>4</sup> Annual Book of ASTM Standards, Vol 01.05

<sup>5</sup> Annual Book of ASTM Standards, Vol 03.01

<sup>6</sup> Available from Standardization Documents Order Desk, Building 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094

<sup>7</sup> Available from American Concrete Institute, P.O. Box 9094, Farmington Hills, MI 48333-9094.