



Standard Specification for Tin Mill Products, General Requirements¹

This standard is issued under the fixed designation A623; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers a group of common requirements, which unless otherwise specified in the purchase order or in an individual specification, shall apply to tin mill products.

1.2 In case of any conflict in requirements, the requirements of the purchase order, the individual material specification, and this general specification shall prevail in the sequence named.

NOTE 1—A complete metric companion to Specification A623 has been developed—Specification A623M; therefore no metric equivalents are presented in this specification.

1.3 The following safety caveat covers [Annex A3](#) through [Annex A10](#) of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)

[A987 Practice for Measuring Shape Characteristics of Tin Mill Products](#)

[D1125 Test Methods for Electrical Conductivity and Resistivity of Water](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E112 Test Methods for Determining Average Grain Size](#)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.20 on Tin Mill Products.

Current edition approved Dec. 1, 2016. Published December 2016. Originally approved in 1968. Last previous edition approved in 2011 as A623 - 11. DOI: 10.1520/A0623-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 U.S. Military Standards:³

[MIL-STD-129 Marking for Shipment and Storage](#)

[MIL-STD-163 Steel Mill Products, Preparation for Marking and Storage](#)

2.3 U.S. Federal Standard:³

[Federal Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)

3. Terminology

3.1 Definitions:

3.1.1 *base box, n*—a unit of area equivalent to 112 sheets 14 by 20 in. or 31 360 in.² (217.78 ft²) (see [Annex A1](#)).

3.1.2 *base weight, n*—a term used to describe the thickness of tin mill products. The designated base weight multiplied by a factor of 0.00011 is the nominal decimal thickness, in inches of the material. Although it is customary industry-wide to use the term “pound” (for example, 75 lb), following the base weight designation, base weight is correctly used only to define nominal material thickness, and is not a measure of the weight of a base box.

3.1.3 *black plate, n*—light-gage, low-carbon, cold-reduced steel intended for use in the untinned state or for the production of other tin mill products. It is supplied only in a dry or oiled condition.

3.1.4 *box annealing, n*—a process involving slow heating of coils to a subcritical temperature, holding, and cooling therefrom, to soften the strip and relieve stresses produced during cold reduction. It is accomplished in a sealed container. By introducing and maintaining an inert or slightly reducing atmosphere during the cycle, a relatively bright surface is obtained.

3.1.5 *bright finish, n*—a surface that has a melted tin coating.

3.1.6 *bundle, n*—a unit containing two or more packages of a cut size, supported by a platform, generally consisting of ten or more packages. (Also commonly referred to as a multiple-package lift containing two or more packages.)

3.1.7 *burr, n*—metal displaced beyond the plane of the surface by slitting or shearing (see [9.1.7](#) and [9.2.6](#)).

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.