



Designation: A 693 – 02^{€1}

Standard Specification for Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip¹

This standard is issued under the fixed designation A 693; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{€1} NOTE—Table 3 was corrected editorially in April 2002.

1. Scope *

1.1 This specification² covers precipitation-hardening stainless steel plate, sheet, and strip. The mechanical properties of these steels are developed by suitable low-temperature heat treatments generally referred to as precipitation hardening.

1.2 These steels are used for parts requiring corrosion resistance and high strength at room temperature or at temperatures up to 600°F (315°C). Some of these steels are particularly suitable for moderate to severe drawing and forming in the solution-treated condition. Others are capable of mild forming only. They are suitable for machining in the solution-annealed condition, after which they may be hardened to the mechanical properties specified in this standard without danger of cracking or distortion.

1.3 The values stated in inch-pound units are to be regarded as the standard.

2. Referenced Documents

2.1 ASTM Standards:

A 480/A 480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip³

E 527 Practice for Numbering Metals and Alloys (UNS)⁴

2.2 SAE Standard:

SAE J 1086 Recommended Practice for Numbering Metals and Alloys (UNS)⁵

3. General Requirements

3.1 The following requirements for orders for material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 480/A 480M or as specified in the following:

3.1.1 Definitions,

3.1.2 General requirements for delivery.

3.1.3 *Ordering Information:*

3.1.3.1 In addition to the requirements of A 480/A 480M, the heat treatment (see 6) must be specified on the purchase order.

4. Materials and Manufacture

4.1 The steel shall be melted by one of the following processes:

4.1.1 Electric furnace (with separate degassing and refining optional),

4.1.2 Vacuum furnace, and

4.1.3 One of the former followed by:

4.1.3.1 Consumable remelting in vacuum, inert gas, or electroslag, or

4.1.3.2 Electron beam refining.

4.1.4 Other commercial melting methods as agreed upon between purchaser and seller are acceptable.

5. Chemical Composition

5.1 The steel shall conform to the requirements as to chemical composition specified in Table 1, and shall conform to applicable requirements specified in the current edition of Specification A 480/A 480M.

6. Heat Treatment of Product

6.1 Material shall be furnished in the solution-annealed condition as noted in Table 2 and Table 3 unless otherwise specified by the purchaser on the purchase order.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel Products.

Current edition approved March 10, 2002. Published April 2002. Originally published as A 693 – 74. Last previous edition A 693 – 01.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-693 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 01.03.

⁴ *Annual Book of ASTM Standards*, Vol 01.01.

⁵ Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.