



Standard Specification for Aluminum Scrap for Use in Deoxidation and Alloying of Steel¹

This standard is issued under the fixed designation A 846; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers aluminum and aluminum alloys in the form of processed scrap designated as shown in Table 1, for use in the manufacture of steel.

1.2 The values stated in inch-pound units are to be regarded as the standard. The metric equivalents of inch-pound units may be approximate.

2. Referenced Documents

2.1 *ASTM Standards*:

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys²

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

- 3.1.1 Quantity,
- 3.1.2 Name or form of material,
- 3.1.3 Size desired,
- 3.1.4 Requirement for packaging, and
- 3.1.5 Reports requested with shipment.

3.2 The basis of payment shall be per pound of alloy.

4. Materials and Manufacture

4.1 The material may be in the form of cut up wire, cans, or other aluminum scrap of suitable purity; or cut up rolled sections, with individual weight tolerance as agreed between the buyer and seller.

4.2 The material may be delivered loose or pressed into pieces, as agreed between buyer and seller. If pressed, the bulk density of individual pieces shall be not less than 0.082 lb/in.³ (85 % of density of pure wrought aluminum). The density of pressed pieces shall be determined as follows:

4.2.1 Each sample piece shall be weighed on a scale capable of accuracy of 1 g weight.

4.2.2 The piece shall be completely sprayed with a lacquer and allowed to dry.

TABLE 1 Chemical and Physical Requirements The usual source of Grade 1W is chopped electrical wire (W); of Grade 1C chopped food cans (C).

Grade (Note 1)	Al, %, min	Mg, %, max	Si, %, max	Zn, %, max	Bulk Density, lb/ft ³ , min (see 4.2)
1W	99.0	...	...	...	90
1C	96.0	2.0	1.0	...	90
1	95.0	1.5	3.0	1.5	90
2	90.0	2.5	5.0	3.0	...

4.2.3 A container of diameter at least twice the size of the tested piece and equipped with an overflow spout shall be filled with water until the overflow ceases; a measuring cylinder capable of ICC accuracy shall be placed under the spout.

4.2.4 The sample piece shall be suspended on a thin wire and gently lowered into the water.

4.2.5 The volume of the overflow, V, shall be read off.

4.2.6 The weight of the sample piece divided by the volume of the overflowed water, g/cc, multiplied by 0.036, is the density of the sample piece, that is $D = W \times 0.036/V$ in lb in.³.

5. Chemical Composition

5.1 The material shall conform to the requirements as to chemical composition and physical properties prescribed in Table 1.

6. Sampling

6.1 If the metal is shipped in carload lots of the same grade, not less than five samples of a minimum of 2 lb each shall be taken at random from the carload for sampling. If the shipment is in less than carload lots, one sample shall be taken for each 6000 lb (2700 kg) or fraction thereof. When it is deemed necessary, a sample may be taken from each melt of 500 lb (230 kg) or more of the alloy.

6.2 If the manufacturer has made an analysis of the material during the course of manufacture, he shall not be required to sample and analyze the finished product.

6.3 If a saw, drill, or cutter is used for taking the sample, it shall be thoroughly cleaned. No lubricant shall be used in the operation, and the sawings or metal chips shall be carefully treated with a magnet to remove any particles of iron introduced in taking the sample.

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved July 26, 1985. Published September 1985.

² *Annual Book of ASTM Standards*, Vol 03.05.