



Standard Guide for Specifying Harmonized Standard Grade Compositions for Wrought Stainless Steels¹

This standard is issued under the fixed designation A959; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This guide provides a guide to ASTM Subcommittees A01.06, A01.10, A01.17, A01.22, and A01.28 for specifying chemical composition limits of wrought stainless steels. It is intended that these recommended grade composition limits be suitable for adoption by other standardization bodies that prepare standards for stainless steel products.

1.2 Included in this guide are the recommendations for determining the number of significant figures for specifying chemical composition from Test Methods, Practices, and Terminology [A751](#).

1.3 All stainless steel UNS numbers and the stainless steel grades in all standards overseen by the aforementioned ASTM subcommittees have been included, except those grades applicable to restricted special end uses and alloys containing less than 10.5 % minimum chromium.

1.4 Not addressed are minor composition modifications which a specific product subcommittee may find necessary to accommodate effects of normal processing or to enhance fabricability by the producer or user, or both.

1.5 Also not generally addressed (except when established by ASTM product subcommittees) is a complete rationalization of all limits, especially when such would conflict with long-standing practices and is not justified by special technical effect.

1.6 Excluded from this guide are cast material and welding filler metal.

2. Referenced Documents

2.1 ASTM Standards:²

[A751](#) Test Methods, Practices, and Terminology for Chemi-

cal Analysis of Steel Products

[E527](#) Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 SAE Standards:³

[J 1086](#) Recommended Practice for Numbering Metals and Alloys

[HS-1086](#) Metals and Alloys in the Unified Numbering System

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *austenitic grade, n*—metallurgical term meaning that the material is usually predominantly face-centered cubic in structure and hardenable only by cold working.

3.1.2 *austenitic-ferritic (duplex) grade, n*—metallurgical term meaning that the material is a mixture of austenitic and ferritic structures, with at least one-fourth of the lesser phase, and hardenable only by cold working.

3.1.3 *ferritic grade, n*—metallurgical term meaning that the material is body-centered cubic in structure (with little, if any, tempered martensite) and hardenable only slightly by cold working (responding little or only slightly to conventional heat treatment by quenching and tempering).

3.1.4 *martensitic grade, n*—metallurgical term meaning that the material is capable of being produced in a distorted body-centered cubic structure by conventional heat treating and quenching, and that the quenched structure is capable of conventional tempering. Martensitic grades are delivered in the annealed (ferritic) condition or the hardened and tempered (martensitic) condition.

3.1.5 *precipitation hardening grade, n*—metallurgical term meaning that the material may be basically austenitic or martensitic in structure and hardenable by precipitation hardening (sometimes called age hardening).

3.1.6 *standard stainless steel grade, n*—listed chemical composition associated with a stainless steel grade identified by a particular UNS number appearing in SAE publication HS-1086, except as modified by an ASTM subcommittee

¹ This guide is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved Sept. 1, 2016. Published October 2016. Originally approved in 1996. Last previous edition approved in 2011 as A959 – 11. DOI: 10.1520/A0959-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

*A Summary of Changes section appears at the end of this standard