



Designation: A1064/A1064M – 17

Standard Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete¹

This standard is issued under the fixed designation A1064/A1064M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers carbon-steel wire and welded wire reinforcement produced from hot-rolled rod to be used for the reinforcement of concrete. The steel wire is cold-worked, drawn or rolled, plain (non-deformed, as-drawn or galvanized), or deformed. Welded wire reinforcement is made from plain or deformed wire, or a combination of plain and deformed wire. Common wire sizes and dimensions are given in [Table 1](#), [Table 2](#), [Table 3](#), and [Table 4](#). Actual wire sizes are not restricted to those shown in the tables.

NOTE 1—Welded wire for concrete reinforcement has historically been described by various terms: welded wire fabric, WWF, fabric, and mesh. The wire reinforcement industry has adopted the term *welded wire reinforcement* (WWR) as being more representative of the applications of the products being manufactured. Therefore, the term *welded wire fabric* has been replaced with the term *welded wire reinforcement* in this specification and in related specifications.

1.2 The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text the SI units are shown in brackets (except in [Table 2](#) and [Table 4](#)). The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values may result in nonconformance with the specification.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved March 15, 2017. Published March 2017. Originally approved in 2009. Last previous edition approved in 2016 as A1064/A1064M – 16b. DOI: 10.1520/A1064_A1064M-17.

2. Referenced Documents

2.1 ASTM Standards:²

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A641/A641M Specification for Zinc-Coated (Galvanized) Carbon Steel Wire

E83 Practice for Verification and Classification of Extensometer Systems

2.2 U.S. Military Standard:³

MIL-STD-129 Marking for Shipment and Storage

2.3 U.S. Military Standard:³

Fed. Std. No. 123 Marking for Shipments (Civil Agencies)

2.4 American Concrete Institute (ACI) Standard:⁴

ACI 318 Building Code Requirements for Structural Concrete

2.5 Adjuncts:

Weld Tester Drawing⁵

3. Terminology

3.1 Definitions of Terms Specific to This Specification:

3.1.1 *convoluted wire*—plain wire for welded wire reinforcement that is formed into a sinusoidal wave shape; deformed wire is not subject to convolution unless agreed upon by the purchaser and manufacturer.

3.1.1.1 *Discussion*—The wire is used in the manufacture of cages for certain applications of concrete pipe reinforcement.

3.1.2 *deformed wire and deformed welded wire reinforcement*—a material composed of cold-worked deformed steel wire as cold-drawn or cold-rolled from hot-rolled steel rod.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

⁴ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

⁵ Available from ASTM International Headquarters. Order Adjunct No. ADJA0185. Original adjunct produced in 1967.

*A Summary of Changes section appears at the end of this standard