



Standard Specification for Welded Austenitic Alloy Steel Boiler, Superheater, Condenser, and Heat Exchanger Tubes with Textured Surface(s)¹

This standard is issued under the fixed designation A1098/A1098M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers average or minimum-wall thickness welded tubes made from various grades of austenitic alloy steel materials in which the (1) external tube surface, (2) internal tube surface, or (3) both internal and external tube surfaces have a textured configuration for improved heat transfer or fluid flow or both. Texture surface(s) are produced by cold forming a specified configuration on the surface(s) of base strip material, prior to welding. The produced welded textured tubes may be used in boilers, superheaters, condensers, evaporators, heat exchangers, and other similar heat transfer apparatus in diameters up to and including 1.5 in. [38 mm] for various wall thicknesses up to and including 0.079 in. [2 mm].

1.2 The tubing sizes and thicknesses usually furnished to this specification are $\frac{3}{8}$ in. [10 mm] inside diameter (ID) to 1.5 in. [38 mm] outside diameter and 0.020 to 0.079 in. [0.5 to 2 mm], inclusive, in wall thickness. Tubing having other dimensions may be furnished provided such tubes comply with all other requirements of this specification.

1.3 Optional supplementary requirements are provided and, when one or more of these are desired, each shall be so stated in the order.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

1.5 The following safety hazards statement pertains only to the test method and the Supplementary Requirements of this specification. A specific warning statement is given in the

Supplementary Requirements. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A249/A249M Specification for Welded Austenitic Steel Boiler, Superheater, Heat-Exchanger, and Condenser Tubes

A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

A1016/A1016M Specification for General Requirements for Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 ASME Standard:³

Boiler and Pressure Vessel Code Section VIII Para UW-51

2.3 SAE Standards:⁴

SAE J1086 Practice for Numbering Metals and Alloys (UNS)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁴ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Nov. 15, 2016. Published January 2017. DOI: 10.1520/A1098_A1098M-16.