

Standard Specification for General Requirements for Steel Plates for Pressure Vessels¹

This standard has been approved for use by agencies of the Department of Defense.

1.1 This specification² covers a group of common requirements which, unless otherwise specified in the individual material specification, shall apply to rolled steel plates for pressure vessels under each of the following specifications issued by ASTM:

Title of Specification	ASTM Designation ³	Pressure Vessel Plates, Low-Carbon Manganese-Molybdenum-Columbium Alloy Steel, for Moderate and Lower Temperature Service	A 735/A 735M
Pressure Vessel Plates, Alloy Steel, Chromium-Manganese Silicon	A 202/A 202M	Pressure Vessel Plates, Low-Carbon Age-Hardening Nickel-Copper-Chromium-Molybdenum-Columbium Alloy Steel	A 736/A 736M
Pressure Vessel Plates, Alloy Steel, Nickel	A 203/A 203M	Pressure Vessel Plates, High-Strength Low-Alloy Steel	A 737/A 737M
Pressure Vessel Plates, Alloy Steel, Molybdenum	A 204/A 204M	Pressure Vessel Plates, Heat-Treated, Carbon-Manganese-Silicon Steel, for Moderate and Lower Temperature Service	A 738/A 738M
Pressure Vessel Plates, Alloy Steel, Manganese-Vanadium	A 225/A 225M	Pressure-Vessel Plates, Quenched and Tempered, Manganese-Chromium-Molybdenum-Silicon-Zirconium Alloy Steel	A 782/A 782M
Pressure Vessel Plates, Carbon Steel, Low- and Intermediate-Tensile Strength	A 285/A 285M	Pressure Vessel Plates, Alloy Steel, Chromium-Molybdenum-Vanadium	A 832/A 832M
Pressure Vessel Plates, Carbon Steel, Manganese-Silicon	A 299/A 299M	Pressure Vessel Plates, Produced by the Thermo-Mechanical Control Process (TMCP)	A 841/A 841M
Pressure Vessel Plates, Alloy Steel, Manganese-Molybdenum and Manganese-Molybdenum-Nickel	A 302/A 302M	Pressure Vessel Plates, 9 % Nickel Alloy, Produced by the Direct-Quenching Process	A 844/A 844M
Pressure Vessel Plates, Alloy Steel, 9 Percent Nickel Double-Normalized and Tempered	A 353/A 353M		
Pressure Vessel Plates, Alloy Steel, Chromium-Molybdenum	A 387/A 387M		
Pressure Vessel Plates, Carbon Steel, High Strength Manganese	A 455/A 455M		
Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service	A 515/A 515M		
Pressure Vessel Plates, Carbon Steel, Moderate- and Lower-Temperature Service	A 516/A 516M		
Pressure Vessel Plates, Alloy Steel, High-Strength, Quenched and Tempered	A 517/A 517M		
Pressure Vessel Plates, Alloy Steel, Quenched and Tempered Manganese-Molybdenum and Manganese-Molybdenum-Nickel	A 533/A 533M		
Pressure Vessel Plates, Heat-Treated, Carbon-Manganese-Silicon Steel	A 537/A 537M		
Pressure Vessel Plates, Alloy Steel, Quenched and Tempered Chromium-Molybdenum	A 542/A 542M		
Pressure Vessel Plates, Alloy Steel, Quenched and Tempered Nickel-Chromium-Molybdenum	A 543/A 543M		
Pressure Vessel Plates, Alloy Steel, Quenched and Tempered 8 and 9 Percent Nickel	A 553/A 553M		
Pressure Vessel Plates, Carbon Steel, Manganese-Titanium for Glass or Diffused Metallic Coatings	A 562/A 562M		
Pressure Vessel Plates, Carbon Steel, High Strength, for Moderate and Lower Temperature Service	A 612/A 612M		

1.1.1 This specification also covers a group of supplementary requirements which are applicable to several of the above specifications as indicated therein. These are provided for use when additional testing or inspection is desired and apply only when specified individually by the purchaser in the order.

1.2 Appendix X1 describes the production and some of the characteristics of coiled product from which pressure vessel plates may be produced.

1.3 Appendix X2 provides information on the variability of tensile properties in plates for pressure vessels.

1.4 Appendix X3 provides information on the variability of Charpy-V-Notch impact test properties in plates for pressure vessels.

1.5 Appendix X4 provides information on cold bending of plates including suggested minimum inside radii for cold bending.

1.6 These materials are intended to be suitable for fusion welding. When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized.

1.7 In case of any conflict in requirements, the requirements

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved October 10, 2001. Published January 2002. Originally published as A 20 – 50 T. Last previous edition A 20/A 20M – 01.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-20/SA-20M in Section II of that Code.

³ These designations refer to the latest issue of the respective specification which appears in the *Annual Book of ASTM Standards*, Vol 01.04.