



Standard Specification for Steel Wire, Oil-Tempered Carbon Valve Spring Quality¹

This standard is issued under the fixed designation A 230/A 230M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers the highest quality of round carbon steel spring wire, uniform in quality and temper, intended especially for the manufacture of valve springs and other springs requiring high-fatigue properties.

1.2 The values stated in either SI (metric) units or inch-pound units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independent of the other.

2. Referenced Documents

2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²

A 510 Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel²

A 510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel [Metric]²

A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment³

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products²

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

2.2 ANSI Standard:

B 32.4M Preferred Metric Sizes for Round, Square, Rectangle, and Hexagon Metal Products⁵

2.3 Military Standard:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage⁶

2.4 Federal Standard:

FED STD No. 123 Marking for Shipment (Civil Agencies)⁶

2.5 AIAG Standard:

AIAGB-5 02.00 Primary Metals Identification Tag Application Standard⁷

3. Ordering Information

3.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of either Specification A 510 or A 510M.

3.2 Orders for material under this specification should include the following information for each ordered item:

3.2.1 Quantity (mass or weight),

3.2.2 Name of material (oil-tempered carbon steel valve spring quality wire),

3.2.3 Dimensions (Section 8),

3.2.4 Chemical composition (Table 1), if required,

3.2.5 Packaging (Section 14),

3.2.6 Cast or heat analysis report, if desired (see 5.2),

3.2.7 Certification or test report, or both, if specified (Section 13), and

3.2.8 ASTM designation and date of issue.

NOTE 1—A typical metric ordering description is as follows: 20 000 kg oil-tempered carbon steel valve spring quality wire, 6.00 mm diameter in 125-kg coils to ASTM A 230M dated ____, or for inch-pound units, 40 000 lb oil-tempered carbon steel valve spring quality wire, 0.250 in. diameter in 350-lb coils to ASTM A 230 dated ____.

4. Materials and Manufacture

4.1 The steel may be made by any commercially accepted steel-making process. The steel may be either ingot cast or strand cast.

4.2 The finished wire shall be free of detrimental pipe and undue segregation.

4.3 The wire shall be hardened and tempered to produce the desired mechanical properties.

5. Chemical Composition

5.1 The steel shall conform to the requirements for chemical composition prescribed in Table 1.

5.2 *Cast or Heat Analysis*—Each cast or heat of steel shall be analyzed by the manufacturer to determine the percentage of

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.03 on Steel Rod and Wire.

Current edition approved March 10, 1999. Published May 1999. Originally published as A 230 – 39 T. Last previous edition A 230/A 230M – 96^{ε1}.

² *Annual Book of ASTM Standards*, Vol 01.03.

³ *Annual Book of ASTM Standards*, Vol 01.05.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

⁵ Available from American National Standards Institute, 11 West 42nd Street, 13th Floor, New York, NY 10036.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁷ Available from the Automotive Industry Action Group, 26200 Lahser, Suite 200, Southfield, MI 48034.