



Designation: A 250/A 250M – 95 (Reapproved 2001)

Standard Specification for Electric-Resistance-Welded Ferritic Alloy-Steel Boiler and Superheater Tubes¹

This standard is issued under the fixed designation A 250/A 250M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers several grades, designated T1, T1a, T1b, T2, T11, T12 and T22, of minimum-wall-thickness, electric-resistance-welded, carbon-molybdenum and chromium-molybdenum alloy-steel, boiler and superheater tubes.

1.2 The tubing sizes and thicknesses usually furnished to this specification are ½ to 5 in. [12.7 to 127 mm] in outside diameter and 0.035 to 0.320 in. [0.9 to 8.1 mm], inclusive, in minimum wall thickness. Tubing having other dimensions may be furnished, provided such tubes comply with all other requirements of this specification.

1.3 Mechanical property requirements do not apply to tubing smaller than ⅛ in. [3.2 mm] in inside diameter or 0.015 in. [0.4 mm] in thickness.

1.4 An optional supplementary requirement is provided and, when desired, shall be so stated in the order.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as the standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

2. Referenced Documents

2.1 ASTM Standards:

A 450/A 450M Specification for General Requirements for Carbon, Ferritic Alloy, and Austenitic Alloy Steel Tubes³

E 213 Practice for Ultrasonic Examination of Metal Pipe and Tubing⁴

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved Sept. 10, 1995. Published December 1995. Originally published as A 250 – 41 T. Last previous edition A 250/A 250M – 91.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SA-250 in Section II of that Code.

³ Annual Book of ASTM Standards, Vol 01.01.

⁴ Annual Book of ASTM Standards, Vol 03.03.

E 273 Practice for Ultrasonic Examination of Longitudinal Welded Pipe and Tubing⁴

3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet, metres, or number of lengths),

3.1.2 Name of material (electric-resistance-welded tubes),

3.1.3 Grade (Table 1),

3.1.4 Size (outside diameter or minimum wall thickness),

3.1.5 Length (specific or random),

3.1.6 Optional requirement (11.6),

3.1.7 Test report required (see Certification Section of Specification A 450/A 450M),

3.1.8 Specification designation, and

3.1.9 Special requirements and any supplementary requirements selected.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 450/A 450M, unless otherwise provided herein.

5. Manufacture

5.1 The steel shall be killed.

5.2 The tubes shall be made by electric-resistance welding.

6. Heat Treatment

6.1 After welding, or when cold finished, after the final cold-drawing pass, all tubes shall be heat treated and, except as provided in 6.1.1, furnished in the full annealed, isothermal annealed, normalized, or normalized and tempered condition at the option of the manufacturer. If furnished in the normalized and tempered condition, the minimum tempering temperature shall be 1200°F [650°C], except T22 shall be tempered at 1250°F [676°C] minimum.

6.1.1 When grades T1, T1a, T1b, and T2 are cold finished, the tubes may, at the option of the manufacturer, be heat treated after the final cold-drawing pass at a temperature of 1200°F or