



**Designation: A 568/A 568M – 02**

An American National Standard

## **Standard Specification for Steel, Sheet, Carbon, and High-Strength, Low-Alloy, Hot- Rolled and Cold-Rolled, General Requirements for<sup>1</sup>**

This standard is issued under the fixed designation A 568/A 568M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### **1. Scope \***

1.1 This specification covers the general requirements for steel sheet in coils and cut lengths. It applies to the following specifications that describe carbon steel and high-strength, low-alloy steel (HSLA) furnished as hot-rolled sheet and cold-rolled sheet: Specifications A 414/A 414M, A 424, A 606, A 659/A 659M, A 794, A 1008/A 1008M, and A 1011/A 1011M.

1.2 This specification is not applicable to hot-rolled heavy-thickness carbon sheet coils (ASTM Specification A 635/A 635M).

1.3 In case of any conflict in requirements, the requirements of the individual material specification shall prevail over those of this general specification.

1.4 For the purposes of determining conformance with this and the appropriate product specification referenced in 1.1, values shall be rounded to the nearest unit in the right hand place of figures used in expressing the limiting values in accordance with the rounding method of Practice E 29.

1.5 Annex A1 lists permissible variations in dimensions and mass (see Note 1) in SI [metric] units. The values listed are not exact conversions of the values listed in the inch-pound tables, but instead are rounded or rationalized values. Conformance to Annex A1 is mandatory when the “M” specification is used.

NOTE 1—The term *weight* is used when inch-pound units are the standard. However, under SI the preferred term is *mass*.

1.6 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.7 This specification and the applicable material specifications are expressed in both inch-pound units and SI units.

However, unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished to inch-pound units.

### **2. Referenced Documents**

#### **2.1 ASTM Standards:**

- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products<sup>2</sup>
- A 414/A 414M Specification for Steel, Sheet, Carbon, for Pressure Vessels<sup>2</sup>
- A 424 Specification for Steel, Sheet, for Porcelain Enameling<sup>2</sup>
- A 606 Specification for Steel, Sheet and Strip, High-Strength, Low-Alloy, Hot-Rolled and Cold-Rolled, with Improved Atmospheric Corrosion Resistance<sup>2</sup>
- A 635/A 635M Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Carbon, Hot-Rolled<sup>2</sup>
- A 659/A 659M Specification for Commercial Steel (CS), Sheet and Strip, Carbon (0.16 Maximum to 0.25 Maximum Percent), Hot-Rolled<sup>2</sup>
- A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment<sup>3</sup>
- A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products<sup>2</sup>
- A 794 Specification for Commercial Steel (CS), Sheet, Carbon (0.16 % Maximum to 0.25 % Maximum), Cold-Rolled<sup>2</sup>
- A 1008/A 1008M Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy and High-Strength Low-Alloy with Improved Formability<sup>2</sup>
- A 1011/A 1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy and High-Strength Low-Alloy with Improved Formability<sup>2</sup>
- E 11 Specification for Wire-Cloth Sieves for Testing Purposes<sup>4</sup>
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>4</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved March 10, 2002. Published April 2002. Originally published as A 568 – 66 T. Last previous edition A 568 – 01.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 01.03.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 14.02.

**\*A Summary of Changes section appears at the end of this standard.**