



Designation: **B 359/B 359M – 9802**

Standard Specification for Copper and Copper-Alloy Seamless Condenser and Heat Exchanger Tubes With Integral Fins¹

This standard is issued under the fixed designation B 359/B 359M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

¹ This specification is under the jurisdiction of ASTM Committee B-5 B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved Oct. 10, ~~1998~~, 2002. Published ~~January 1999~~, December 2002. Originally published as B 359 – 60; approved in 1960. Last previous edition approved in 1998 as B 359 – 958.

1. Scope *

1.1 This specification² ~~describes~~ establishes the requirements for seamless copper and copper alloy tubing on which the external or internal surface, or both, has been modified by a cold-forming process to produce an integral enhanced surface for improved heat transfer.

1.2 Units—The values stated in either in-pound units or SI units are to be regarded separately as the standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems could result in nonconformance with the specification.

1.3 The tubes are typically used in surface condensers, evaporators, and heat ~~exchangers and are normally made from exchangers.~~

1.4 The product shall be produced of the following coppers or copper alloys—~~alloys, as specified in the ordering information.~~

Copper or Copper Alloy UNS No.	Type of Metal
C10100	Oxygen-free electronic
C10200	Oxygen-free without residual deoxidants
C10300	Oxygen-free, extra low phosphorus
C10800	Oxygen-free, low phosphorus
~~E12000~~	~~DLP Phosphorized, low residual phosphorus~~
<u>C12000</u>	<u>DLP Phosphorized, low residual phosphorus</u>
	(See Note 1)
~~E12200~~	~~DHP, Phosphorized, high residual phosphorus~~
<u>C12200</u>	<u>DHP, Phosphorized, high residual phosphorus</u>
	(See Note 1)
~~E14200~~	~~DPA Phosphorized arsenical~~
<u>C14200</u>	<u>DPA Phosphorized arsenical</u>
	(See Note 1)
C19200	Phosphorized, 1 % iron
C23000	Red Brass
C44300	Admiralty Metal Types B,
C44400	C, and
C44550	D
C60800	Aluminum Bronze
C68700	Aluminum Brass Type B
C70400	95-5 Copper-Nickel
C70600	90-10 Copper-Nickel
<u>C70620</u>	<u>90-10 Copper-Nickel (Modified for Welding)</u>
C71000	80-20 Copper-Nickel Type A
C71500	70-30 Copper-Nickel
<u>C71520</u>	<u>70-30 Copper-Nickel (Modified for Welding)</u>
C72200	Copper-Nickel

NOTE 1—~~Refer to Practice E 527 for explanation of Unified Numbering System (UNS).~~

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-359 in Section II of that Code.

***A Summary of Changes section appears at the end of this standard.**