



Standard Specification for Concentric-Lay-Stranded Aluminum Conductors, Aluminum- Clad Steel Reinforced for Use in Overhead Electrical Conductors¹

This standard is issued under the fixed designation B549; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers concentric-lay-stranded conductors made from round aluminum 1350-H19 (extra hard) aluminum wires and round aluminum-clad steel core wires for use as overhead electrical conductors (Explanatory **Note 1** and **Note 2**).

1.2 The SI values of density and resistivity are to be regarded as standard. For all other properties the inch-pound units are regarded as standard and the SI units may be approximate.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein.

2.2 ASTM Standards:²

B230/B230M Specification for Aluminum 1350–H19 Wire for Electrical Purposes

B263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors

B354 Terminology Relating to Uninsulated Metallic Electrical Conductors

B500/B500M Specification for Metallic Coated or Aluminum Clad Stranded Steel Core for Use in Overhead Electrical Conductors

B502 Specification for Aluminum-Clad Steel Core Wire for Use in Overhead Electrical Aluminum Conductors

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.07 on Conductors of Light Metals.

Current edition approved April 1, 2013. Published May 2013. Originally approved in 1971. Last previous edition approved in 2010 as B549 – 10. DOI: 10.1520/B0549-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.3 ANSI Standards:³

ANSI C 42.100 Dictionary of Electrical and Electronics Terms

ANSI H 35.1 American National Standard Alloy and Temper Designation Systems for Aluminum

2.4 Other Standard:

NBS Handbook 100—Copper Wire Tables of the National Bureau of Standards⁴

3. Terminology

3.1 Description of Terms Specific to This Standard

3.1.1 ACSR covered by this specification has one type of steel core wire which is designated by the following abbreviation (Explanatory **Note 2**):

3.1.1.1 ACSR/AW—ACSR using aluminum-clad steel wire (Explanatory **Note 2**).

4. Classification

4.1 For the purpose of this specification, conductors are classified as follows (Explanatory **Note 1** and **Note 2**):

4.1.1 *Class AA*—For bare conductors usually used in overhead lines. These conductors are used as follows:

4.1.1.1 Conductors used for regular overhead line construction and

4.1.1.2 Conductors having a high ratio of mechanical strength to current-carrying capacity used for overhead ground wires and for extra-long span construction.

4.1.2 *Class A*—For conductors to be covered with weather-resistant (weatherproof) materials.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 Quantity of each size, stranding, and class,

5.1.2 Conductor size: circular mil area or AWG of aluminum wires (Section 9 and Table 1),

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from National Technical Information Service (NTIS), 5301 Shawnee Rd., Alexandria, VA 22312, <http://www.ntis.gov>.