



Designation: B 550/B 550M – 012

Standard Specification for Zirconium and Zirconium Alloy Bar and Wire¹

This standard is issued under the fixed designation B 550/B 550M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.02 on Zirconium and Hafnium.

Current edition approved ~~Nov.~~ Oct. 10, 20012. Published ~~January~~ December 2002. Originally published as B 550 – 71. Last previous edition B 550/B 550M – 9701.

1. Scope

1.1 This specification² covers three grades of zirconium and zirconium alloy bar and wire.

1.2 Unless a single unit is used, for example corrosion mass gain in mg/dm², the values stated in either inch-pound or SI units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore each system must be used independently of the other. SI values cannot be mixed with inch-pound values.

1.3 The following precautionary caveat pertains only to the test methods portions of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

E 8 Test Methods for Tension Testing of Metallic Materials³

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *annealed*—denotes material that exhibits a recrystallized grain structure.

3.2 *Lot Definitions:*

3.2.1 *castings*—a lot shall consist of all castings produced from the same pour.

3.2.2 *ingot*—no definition required.

3.2.3 *rounds, flats, tubes, and wrought powder metallurgical products (single definition, common to nuclear and non-nuclear standards)*—a lot shall consist of a material of the same size, shape, condition, and finish produced from the same ingot or powder blend by the same reduction schedule and the same heat treatment parameters. Unless otherwise agreed between manufacturer and purchaser, a lot shall be limited to the product of an 8 h period for final continuous anneal, or to a single furnace load for final batch anneal.

3.2.4 *sponge*—a lot shall consist of a single blend produced at one time.

3.2.5 *weld fittings*—definition is to be mutually agreed upon between manufacturer and the purchaser.

4. Classification

4.1 The bar or wire is to be furnished in three grades as follows:

4.1.1 *Grade R60702*—Unalloyed zirconium.

4.1.2 *Grade R60704*—Zirconium-tin.

4.1.3 *Grade R60705*—Zirconium-niobium.

5. Ordering Information

5.1 Orders for material under this specification should include the following information:

5.1.1 Quantity (weight or number of pieces),

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-550 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.