



Standard Specification for Pure Palladium Electrical Contact Material¹

This standard is issued under the fixed designation B 683; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense. Consult the DoD Index of Specifications and Standards for the specific year of issue which has been adopted by the Department of Defense.

^{€1} NOTE—Section 8 was added editorially in June 1995.

1. Scope

1.1 This specification covers palladium in the form of rod, wire, strip, and sheet material for electrical contacts.

1.2 The values stated in inch-pound units are to be regarded as the standard. The metric equivalents of inch-pound units may be approximate.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 It is the responsibility of the user to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer.

2. Referenced Documents

2.1 *ASTM Standards:*

B 476 Specification for General Requirements for Wrought Precious Metal Electrical Contact Materials²

B 589 Specification for Refined Palladium³

3. Manufacture

3.1 Raw materials shall be of such quality and purity that the finished product will have the properties and characteristics prescribed in this specification.

3.2 The material shall be finished by such operations (cold working, annealing, turning, grinding, or pickling) as are required to produce the prescribed properties.

4. Chemical Composition

4.1 Material produced under this specification shall meet the requirements of chemical composition prescribed in Table 1.

NOTE 1—The chemical requirements for unfabricated palladium (re-

TABLE 1 Chemical Requirements

Element	Weight, %
Pd	99.8 min
Total impurities	0.2 max
Pt group (Ir, Pt, Rh, Os, Ru) and Au, Ag, Cu	0.1 max
Total other impurities (within the following limits)	0.1 max
Pb, Sb, Bi, Sn, As, Cd, Zn	0.01 max each
Fe	0.015 max
Other elements	0.02 max each

finished material) are covered in Specification B 589.

4.2 By agreement between the purchaser and the manufacturer, analysis may be required and limits established for elements or compounds not specified in the table of chemical composition.

5. Mechanical Requirements

5.1 The criterion for temper designation shall be one of the following: Rockwell, Rockwell superficial, microhardness (Vickers or Knoop), or tensile strength (hardness or tension, but not both) as defined in the contract or order.

5.2 Mechanical properties shall conform to the listings of Table 2.

5.3 Since it is not always possible to tension test some parts and shapes, the user and supplier should reach an agreement with respect to the type of hardness tests and the acceptable range that should be applicable. See Table 3 for typical hardness values.

5.4 All test specimens shall be full size when practical.

5.5 All tests shall be conducted at room temperature, 65 to 85°F (18 to 29°C).

6. General Requirements

6.1 The provisions of Specification B 476 shall apply to all materials produced to this specification.

7. Inspection and Testing

7.1 Material furnished under this specification shall be inspected by the manufacturer as listed below:

7.1.1 Visual inspection in accordance with 12.2.1 in Specification B 476.

¹ This specification is under the jurisdiction of ASTM Committee B-4 on Metallic Materials for Thermostats and for Electrical Resistance, Heating, and Contacts and is the direct responsibility of Subcommittee B04.02 on Electrical Contact Materials.

Current edition approved May 25, 1990. Published November 1990. Originally published as B 683 – 80. Last previous edition B 683 – 80 (1985).

² *Annual Book of ASTM Standards*, Vol 03.04.

³ *Annual Book of ASTM Standards*, Vol 02.04.