



Standard Specification for Nickel-Iron-Chromium-Silicon Alloy Welded Tube¹

This standard is issued under the fixed designation B 739; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers alloys UNS N08330 and UNS N08332 in the form of welded tube intended for heat resisting applications and general corrosive service.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- B 536 Specification for Nickel-Iron-Chromium-Silicon Alloys (UNS N08330 and N08332) Plate, Sheet, and Strip²
- B 751 Specification for General Requirements for Nickel and Nickel Alloy Welded Tube²

3. General Requirement

3.1 Material furnished under this specification shall conform to the applicable requirements of Specification B 751 unless otherwise provided herein.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

4.1.1 Alloy (Table 1),

4.1.2 ASTM designation and year of issue,

4.1.3 Dimensions (outside or inside diameter and nominal wall thickness),

4.1.4 Length (specific or random),

4.1.5 Quantity (feet or number of pieces),

4.1.6 *Certification*—State if certification is required,

4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished, and

4.1.8 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

5. Materials and Manufacture

5.1 The tube shall be made from flat-rolled alloy conforming to Specification B 536, by an automatic welding process with no addition of filler metal. Subsequent to welding and prior to final heat treatment, the tube shall be cold-worked either in both weld and base metal or in weld metal only.

6. Chemical Composition

6.1 The material shall conform to the requirements, as to chemical composition specified in Table 2.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations per Specification B 751.

7. Mechanical Properties and Other Requirements

7.1 The tensile properties of the material at room temperature shall conform to those shown in Table 1.

7.2 *Grain Size*—Annealed Alloy UNS N08332 shall conform to an average grain size of ASTM No. 5 or coarser.

7.3 *Annealing Temperature*—Alloy UNS N08330 shall be annealed at 1900°F (1040°C) minimum. Alloy UNS N08332 shall be annealed at 2050°F (1120°C) minimum.

8. Keywords

8.1 welded tube; N08330; N08332

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved June 10, 2003. Published July 2003. Originally approved in 1985. Last previous edition approved in 1998 as B 739 - 98.

² *Annual Book of ASTM Standards*, Vol 02.04.