



Standard Test Method for Measuring Volume of Apparent Density Cup Used in Test Methods B 212, B 329, and B 417¹

This standard is issued under the fixed designation B 873; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a procedure for measuring the volume of the apparent density cups used in Test Methods B 212, B 329, and B 417.

1.2 The apparent density cup, particularly its rim, may become worn during use, and it is recommended that the volume of the cup be checked periodically (at least every 6 months) in order to ensure that it complies with the specified volume.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

B 212 Test Method for Apparent Density of Free-Flowing Metal Powders Using the Hall Flowmeter Funnel²

B 243 Terminology of Powder Metallurgy²

B 329 Test Method for Apparent Density of Metal Powders and Compounds Using the Scott Volumeter²

B 417 Test Method for Apparent Density of Non-Free-Flowing Metal Powders Using the Carney Funnel²

3. Terminology

3.1 **Definitions**—Definitions of powder metallurgy terms can be found in Terminology B 243. Additional descriptive information is available in the Related Materials section of Vol 02.05 of the *Annual Book of ASTM Standards*.

4. Summary of Test Method

4.1 The apparent density cup is filled with water and weighed to obtain the mass of water contained, which is then converted to a volume.

5. Significance and Use

5.1 This test method enables the measurement of the volume of the apparent density cup to ensure that it complies with the specified volume of $25.00 \pm 0.03 \text{ cm}^3$ (cylindrical cup), or $16.39 \pm 0.05 \text{ cm}^3$ (square cup). Use of an out-of-specification cup will give erroneous apparent density values using the formulae in Test Methods B 212, B 329, and B 417.

6. Apparatus

6.1 **Density Cup**—A cylindrical cup (see Fig. 1) designed to have a capacity of $25.00 \pm 0.03 \text{ cm}^3$ (as in Test Methods B 212, B 329, and B 417) or a square cup designed to have a capacity of $16.39 \pm 0.05 \text{ cm}^3$ (as in Test Method B 329).

6.2 **Balance**, suitable for weighing at least 200 g to the nearest 0.001 g.

6.3 **Microscope Slide**—A transparent microscope slide at least as wide as the outer diameter of the apparent density cup.

6.4 **Water**—Distilled or deionized water boiled to remove dissolved air.

6.5 **Alcohol**—Low residue ethyl alcohol.

6.6 **Wire**—A wire not exceeding 2.5 mm in diameter by 150 mm long.

6.7 **Thermometer**—A thermometer capable of measuring the temperature of the water to the nearest 1°C.

7. Procedure

7.1 Boil at least 150 mL of distilled or deionized water for 5 min to remove dissolved air. Cool to room temperature and handle so as to avoid the introduction of air bubbles.

7.2 Clean the density cup with alcohol and dry thoroughly.

7.3 Weigh, to the nearest 0.001 g, the density cup along with a clean, clear microscope slide. This is the tare mass, T .

7.4 Fill the density cup with the prepared water until the water overflows.

7.5 Dislodge any air bubbles inside the density cup with a clean wire.

7.6 Slide the clean, clear microscope slide horizontally across the rim of the density cup, spilling the excess water over the sides of the cup and center the microscope slide on top of the cup.

7.7 If any air bubbles appear, remove the microscope slide and return to 7.4.

¹ This test method is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.02 on Base Metal Powders.

Current edition approved Nov. 10, 2001. Published January 2002. Originally published as B 873 – 96. Last previous edition B 873 – 96.

² *Annual Book of ASTM Standards*, Vol 02.05.