



Standard Terminology of Ceramic Whitewares and Related Products¹

This standard is issued under the fixed designation C242; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology pertains to the terminology used in ceramic whitewares and related products.

1.2 Words adequately defined in standard dictionaries are not included. Included are words that are peculiar to this industry. Double words, hyphenated words, or phrases are listed alphabetically under the first word; additional important words are cross-referenced.

1.3 For definitions of terms relating to surface imperfections on ceramics, refer to Terminology **F109**.

2. Referenced Documents

2.1 *ASTM Standards*:²

D1129 Terminology Relating to Water

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³

F109 Terminology Relating to Surface Imperfections on Ceramics

F465 Practice for Developing Precision and Accuracy Data on ASTM Method for the Analysis of Meat and Meat Products (Withdrawn 1993)³

2.2 *British Standard*:⁴

BS 2955 Glossary of Terms Relating to Powders

3. Terminology

absolute or true density—See *absolute or true density* under **density**.

¹ This terminology is under the jurisdiction of ASTM Committee **C21** on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee **C21.01** on Editorial and Terminology.

Current edition approved March 1, 2015. Published March 2015. Originally approved in 1950. Last previous edition approved in 2014 as C242 – 14. DOI: 10.1520/C0242-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from British Standards Institute, 2 Park St., London, England W1A 2BS.

absorbance—the logarithm of that fraction of an incident light beam that is dissipated in the sample, being neither transmitted nor reflected.

absorbed moisture—water held mechanically in the material and having physical properties not substantially different from ordinary water at the same temperature and pressure.

absorption—(1) the relationship of the weight of the water absorbed by a ceramic specimen, subjected to prescribed immersion procedure, to the weight of the dry specimen.

(2) the capacity of a substance to take up a substance, usually a liquid or gas, with the formation of an apparently homogeneous mixture.

adsorption—the capacity of a substance to accept and retain on its surface a layer of another substance, usually a gas or a liquid.

agglomerate—a jumbled mass or collection of two or more particles or aggregates, or a combination thereof, held together by relatively weak cohesive forces caused by weak chemical bonding or an electrostatic surface charge generated by handling or processing.

DISCUSSION—Common usage in powder technology (and British Standard BS 2955) has the terms “aggregate” and “agglomerate” interchanged in meaning from the definitions presented here, and care must be taken to determine in context which definition is in use.

aggregate—a dense mass of particles held together by strong intermolecular or atomic cohesive forces that is stable to normal mixing techniques, including high-speed stirring and ultrasonics.

alumina porcelain—See *alumina porcelain* under **porcelain**.

alumina whiteware—See *alumina whiteware* under **ceramic whiteware**.

andalusite—a polymorph, along with sillimanite and kyanite, of composition $\text{Al}_2\text{O}_3 \cdot \text{SiO}_2$ which on firing dissociates to yield principally mullite.

apparent or pycnometric density—See *apparent or pycnometric density* under **density**.

apparent porosity—See *apparent porosity* under **porosity**.

average particle size—a single value representing the entire particle-size distribution.

DISCUSSION—It is essential to specify the basis under which the average is obtained.