Designation: C494/C494M – 16

Standard Specification for Chemical Admixtures for Concrete[1]

This standard is issued under the fixed designation C494/C494M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers materials for use as chemical admixtures to be added to hydraulic-cement concrete mixtures in the field for the purpose or purposes indicated for the eight types as follows:

1.1.1 *Type A*—Water-reducing admixtures,

1.1.2 *Type B*—Retarding admixtures,

1.1.3 *Type C*—Accelerating admixtures,

1.1.4 *Type D*—Water-reducing and retarding admixtures,

1.1.5 *Type E*—Water-reducing and accelerating admixtures,

1.1.6 *Type F*—Water-reducing, high range admixtures,

1.1.7 *Type G*—Water-reducing, high range, and retarding admixtures, and

1.1.8 *Type S*—Specific performance admixtures.

1.2 This specification stipulates tests of an admixture with suitable concreting materials as described in 11.1 – 11.3 or with cement, pozzolan, aggregates, and an air-entraining admixture proposed for specific work (11.4). Unless specified otherwise by the purchaser, the tests shall be made using concreting materials as described in 11.1 – 11.3.

NOTE 1—It is recommended that, whenever practicable, tests be made using the cement, pozzolan, aggregates, air-entraining admixture, and the mixture proportions, batching sequence, and other physical conditions proposed for the specific work (11.4) because the specific effects produced by chemical admixtures may vary with the properties and proportions of the other ingredients of the concrete. For instance, Types F and G admixtures may exhibit much higher water reduction in concrete mixtures having higher cement factors than that listed in 12.1.1.

Mixtures having a high range water reduction generally display a higher rate of slump loss. When high-range admixtures are used to impart increased workability (6 to 8-in. slump [150 to 200–mm]), the effect may be of limited duration, reverting to the original slump in 30 to 60 min depending on factors normally affecting rate of slump loss. The use of chemical admixtures to produce high-slump (flowing) concrete is covered by Specification C1017/C1017M.

NOTE 2—The purchaser should ensure that the admixture supplied for use in the work is equivalent in composition to the admixture subjected to test under this specification (see Section 6, Uniformity and Equivalence).

NOTE 3—Admixtures that contain relatively large amounts of chloride may accelerate corrosion of prestressing steel. Compliance with the requirements of this specification does not constitute assurance of acceptability of the admixture for use in prestressed concrete.

1.3 This specification provides for three levels of testing.

1.3.1 *Level 1*—During the initial approval stage, proof of compliance with the performance requirements defined in Table 1 demonstrates that the admixture meets the requirements of this specification. Admixtures (except for Types B, C, E, and S) shall qualify for provisional compliance when the physical requirements and any of the alternative compressive strength requirements in Table 1 are met. If subsequent test results at six months or one year fail to meet the standard requirement of 100 % of reference strength, the compliance of the admixture to this standard is withdrawn and all users of the admixture shall be notified immediately. Uniformity and equivalence tests of Section 6 shall be carried out to provide results against which later comparisons can be made (see Note 4).

NOTE 4—Allowing for provisional compliance while retaining longer term compressive strength requirements promotes more rapid qualification of new materials, but also provides assurance that new admixture technologies will not exhibit unexpected longer term performance. The alternative compressive strength requirements in Table 1 are based on statistical analysis of 103 Specification C494/C494M evaluation tests. The alternative requirements correspond to a 99 % probability of passing subsequent test age requirements.[2]

1.3.2 *Level 2*—Limited retesting is described in 5.2 – 5.2.2. Proof of compliance with the requirements of Table 1 demonstrates continued conformity of the admixture with the requirements of the specification.

1.3.3 *Level 3*—For acceptance of a lot or for measuring uniformity within or between lots, when specified by the purchaser, the uniformity and equivalence tests of Section 6 shall be used.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

[1] This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.23 on Chemical Admixtures.

Current edition approved July 1, 2016. Published August 2016. Originally approved in 1962. Last previous edition approved in 2015 as C494/C494M – 15a. DOI: 10.1520/C0494_C0494M-16.

[2] Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C09-1030.

***A Summary of Changes section appears at the end of this standard**

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States