



Standard Test Method for Compressive Stress of Porcelain Enamels by Loaded-Beam Method¹

This standard is issued under the fixed designation C839; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Many methods and tests have been used in the industry to determine the relative compressive stress of porcelain enamel ground coats and cover coats. Three methods have been most commonly used. They are loaded-beam, warp, and split-ring methods. In the loaded-beam method the measure of stress is the load required to bring a specimen back to a plane after it has been bowed by controlled application of the enamel under test to one side of the specimen. The degree of the deflection of a specimen from a plane caused by controlled application of enamel to one side is the indicating measure of stress in the warp test. The indicating measurement in the split-ring test is the force required to just open a split ring after controlled application of test enamel to the outside surface of a ring.

1. Scope

1.1 This test method covers the measurement of the compressive stresses ([Note 1](#)) developed by fired porcelain enamels using the loaded-beam method.

NOTE 1—Although some may interpret the calculations that are used in this test method as indicating compressive load, it is commonly referred to as compressive stress within the porcelain enamel industry.

1.2 This test method is limited to the use of the loaded-beam method. However, this method includes charts ([Fig. 1](#) and [Fig. 2](#)) that provide for conversion of loaded-beam test results to warp and ring stress values.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.12 on Materials for Porcelain Enamel and Ceramic-Metal Systems.

This test method was developed at the National Bureau of Standards under the sponsorship of the Porcelain Enamel Institute, Inc., and was published as PEI Technical Publication No. T-30 (1973).

Current edition approved May 1, 2015. Published June 2015. Originally approved in 1976. Last previous edition approved in 2010 as C839 – 82(2010). DOI: 10.1520/C0839-82R15.

2. Referenced Documents

2.1 *ASTM Standards*:²

A424 Specification for Steel, Sheet, for Porcelain Enameling

3. Terminology

3.1 *Description of Term Specific to This Standard*

3.2 *compressive stress or stress*—a term used to designate the degree of compression that exists in a porcelain enamel on steel after processing.

4. Significance and Use

4.1 All porcelain enamel coatings or glass coatings are by necessity under some degree of compression at room temperature. The desired degree of compression or stress depends upon the type of ware and the end use of the item. Some method of determining relative compressive stress of enamels is necessary to establish the suitability of an enamel for a proposed application.

5. Apparatus

5.1 *Furnace*, suitable for simultaneous firing of at least six 1 by 12-in. (25 by 305-mm) specimens in vertical hanging position.

5.2 *Firing Rack*, suitable for furnace.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.