



Standard Specification for Cellulosic Fiber Stabilized Thermal Insulation¹

This standard is issued under the fixed designation C1497; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the composition and physical properties of spray-applied cellulosic fiber stabilized thermal insulation applied to open or closed ceiling spaces, regardless of slope, where temperatures range from -49 to 194°F (-45 to 90°C).

1.2 Stabilized cellulosic fiber thermal insulation is produced by the addition of adhesive(s) to loose-fill cellulosic fiber insulation. The adhesive(s) are either added to the insulation at time of manufacture and, if necessary, activated by the addition of water when installed or the adhesive(s) are otherwise added to the insulation at the time of installation.

1.3 This is a material specification that is not intended to deal with methods of application that are supplied by the manufacturer.

1.4 The values stated in inch-pound units are to be regarded as standard. The SI units given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations

C168 Terminology Relating to Thermal Insulation

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved Oct. 1, 2016. Published October 2016. Originally approved in 2001. Last previous edition approved in 2012 as C1497 – 12. DOI: 10.1520/C1497-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C739 Specification for Cellulosic Fiber Loose-Fill Thermal Insulation

C1149 Specification for Self-Supported Spray Applied Cellulosic Thermal Insulation

C1304 Test Method for Assessing the Odor Emission of Thermal Insulation Materials

C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E970 Test Method for Critical Radiant Flux of Exposed Attic Floor Insulation Using a Radiant Heat Energy Source

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, see Terminology **C168**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *shrinkage*—decrease in thickness that occurs from the time of installation until the insulation is dry (see 7.2.5).

3.2.2 *stabilized cellulose*—a cellulosic insulation product treated to resist, after drying, further settling of no more than 5 %.

4. Materials and Manufacture

4.1 The basic material shall be recycled cellulosic fiber made from selected paper or paperboard stock. Additives are introduced to affect different performance characteristics, including those related to fire performance, processing, and handling. An adhesive is added to the insulation product to resist long-term settling of the insulation after installation and curing.

4.2 The materials are processed into a form suitable for installation by a pneumatic method.

4.3 The adhesive is added to the product either at the time of manufacture or at the time of installation by means of a liquid spray.

5. Physical and Chemical Properties

5.1 *Density*—The density of conditioned stabilized insulation in lb/ft^3 (kg/m^3) shall be determined in accordance with Section 7.

5.2 *Corrosiveness*—The loose-fill insulation material shall be tested for corrosiveness in accordance with Section 8. The