



Standard Test Method for Determining the Apparent Chloride Diffusion Coefficient of Cementitious Mixtures by Bulk Diffusion¹

This standard is issued under the fixed designation C1556; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the laboratory determination of the apparent chloride diffusion coefficient for hardened cementitious mixtures.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field

C42/C42M Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete

C125 Terminology Relating to Concrete and Concrete Aggregates

C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C1152/C1152M Test Method for Acid-Soluble Chloride in Mortar and Concrete

C1202 Test Method for Electrical Indication of Concrete's Ability to Resist Chloride Ion Penetration

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.66 on Concrete's Resistance to Fluid Penetration.

Current edition approved April 1, 2016. Published May 2016. Originally approved in 2003. Last previous edition approved in 2011 as C1556 – 11a. DOI: 10.1520/C1556-11AR16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 NORDTEST Standards:

NT BUILD 443 Approved 1995-11, Concrete, Hardened: Accelerated Chloride Penetration (in English)³

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminology C125.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *apparent chloride diffusion coefficient, D_w* , n —a chloride transport parameter calculated from acid-soluble chloride profile data obtained from saturated specimens exposed to chloride solutions, without correction for chloride binding, that provides an indication of the ease of chloride penetration into cementitious mixtures.

3.2.2 *chloride binding, v* —the chemical process by which chloride ion is removed from solution and incorporated into cementitious binder hydration products.

3.2.2.1 *Discussion*—Chloride binding is primarily associated with hydration products formed by the aluminate phase of cement and mixtures containing ground granulated blast furnace slag.

3.2.3 *chloride penetration, v* —the ingress of chloride ions due to exposure to external sources.

3.2.4 *exposure liquid, n* —the sodium chloride solution in which test specimens are stored prior to obtaining a chloride profile.

3.2.5 *exposure time, n* —the time that the test specimen is stored in the solution containing chloride ion.

3.2.6 *initial chloride-ion content, C_i* , n —the ratio of the mass of chloride ion to the mass of concrete for a test specimen that has not been exposed to external chloride sources.

3.2.7 *profile grinding, v* —the process of grinding off and collecting a powder sample in thin successive layers from a test specimen using a dry process.

³ Published by NORDTEST, P.O. Box 116 FIN-02151 ESPOO Finland, Project 1154-94, e-mail: nordtest@vtt.fi, website: <http://www.vtt.fi/nordtest>