



Designation: D664 – 18^{ε2}

British Standard 4457

Designation 177/96

Standard Test Method for Acid Number of Petroleum Products by Potentiometric Titration¹

This standard is issued under the fixed designation D664; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Subsection 13.3.1 and a statement in the Summary of Changes were corrected editorially in December 2018.

^{ε2} NOTE—Subsections 16.1.1.1 and 16.1.2.1 were corrected editorially in January 2019.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers procedures for the determination of acidic constituents in petroleum products, lubricants, biodiesel, and blends of biodiesel.

1.1.1 *Test Method A*—For petroleum products and lubricants soluble or nearly soluble in mixtures of toluene and propan-2-ol. It is applicable for the determination of acids whose dissociation constants in water are larger than 10^{-9} ; extremely weak acids whose dissociation constants are smaller than 10^{-9} do not interfere. Salts react if their hydrolysis constants are larger than 10^{-9} . The range of acid numbers included in the precision statement is 0.1 mg/g KOH to 150 mg/g KOH.

1.1.2 *Test Method B*—Developed specifically for biodiesel and biodiesel blends with low acidity and slightly different solubility. This test method requires the use of an automatic titrator with automatic endpoint-seeking capability.

NOTE 1—In new and used oils, the constituents that may be considered to have acidic characteristics include organic and inorganic acids, esters, phenolic compounds, lactones, resins, salts of heavy metals, salts of ammonia and other weak bases, acid salts of polybasic acids, and addition agents such as inhibitors and detergents.

1.2 The test method may be used to indicate relative changes that occur in oil during use under oxidizing conditions regardless of the color or other properties of the resulting oil. Although the titration is made under definite equilibrium conditions, the test method is not intended to measure an absolute acidic property that can be used to predict performance of oil under service conditions. No general relationship between bearing corrosion and acid number is known.

NOTE 2—The acid number obtained by this standard may or may not be numerically the same as that obtained in accordance with Test Methods D974 and D3339. There has not been any attempt to correlate this method with other non-titration methods.

NOTE 3—A few laboratories have made the observation that there is a difference in Test Method D664 results when aqueous versus nonaqueous buffers are used.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D974 Test Method for Acid and Base Number by Color-Indicator Titration
- D1193 Specification for Reagent Water
- D3339 Test Method for Acid Number of Petroleum Products by Semi-Micro Color Indicator Titration
- D4057 Practice for Manual Sampling of Petroleum and Petroleum Products
- D4177 Practice for Automatic Sampling of Petroleum and Petroleum Products

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.06 on Analysis of Liquid Fuels and Lubricants.

Current edition approved Nov. 1, 2018. Published November 2018. Originally approved in 1942. Last previous edition approved in 2017 as D664 – 17a. DOI: 10.1520/D0664-18E02.

This test method was adopted as a joint ASTM-IP standard in 1964. ASTM Test Method D4739 has been developed as an alternative to the base number portion of D664.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard