



Standard Test Methods for Analysis of Magnesium Silicate Pigment¹

This standard is issued under the fixed designation D 717; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the analysis of magnesium silicate pigment.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address the safety concerns associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 234 Specification for Raw Linseed Oil²

D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments²

D 718 Test Methods for Analysis of Aluminum Silicate Pigment²

D 1193 Specification for Reagent Water³

D 1208 Test Methods for Common Properties of Certain Pigments²

D 2448 Test Method for Water-Soluble Salts in Pigments by Measuring the Specific Resistance of the Leachate of the Pigment²

E 97 Test Method for Directional Reflectance Factor, 45-deg 0-deg, of Opaque Specimens by Broad-Band Filter Reflectometry⁴

3. Significance and Use

3.1 These test methods may be used to confirm the stated SiO₂, CaO, and MgO content of magnesium silicate for quality control.

4. Apparatus

4.1 *Platinum Crucible.*

4.2 *Electric Furnace, capable of 1200°C.*

5. Purity of Reagents

5.1 Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁵ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 Unless otherwise indicated, references to water shall be understood to mean Type II of Specification D 1193.

SILICON DIOXIDE

6. Reagents

6.1 *Hydrochloric Acid* (sp gr 1.19)—Concentrated hydrochloric acid (HCl).

6.2 *Hydrochloric Acid* (1+20)—Mix 1 volume of concentrated hydrochloric acid (HCl, sp gr 1.19) with 20 volumes of water.

6.3 *Hydrofluoric Acid* (48 %)—Concentrated hydrofluoric acid (HF).

6.4 *Sodium Carbonate* (Na₂CO₃).

6.5 *Sulfuric Acid* (sp gr 1.84)—Concentrated sulfuric acid (H₂SO₄).

7. Procedure

7.1 Transfer 1 g of the sample weighed to 0.1 mg to a platinum crucible and fuse with 5 g of Na₂CO₃ until the entire contents of the crucible are in a molten state. Continue heating for 20 min. Keep a close-fitting platinum cover on the crucible

¹ These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 1, 2003. Published October 2003. Originally approved in 1943. Last previous edition approved in 1986 as D 717 - 86 (1999).

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 11.01.

⁴ Discontinued; see 1992 *Annual Book of ASTM Standards*, Vol 14.02.

⁵ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.