



Designation: D 941 - 88

AMERICAN SOCIETY FOR TESTING AND MATERIALS

1916 Race St., Philadelphia, Pa. 19103

Reprinted from the Annual Book of ASTM Standards, Copyright ASTM
If not listed in the current combined index, will appear in the next edition.

An American National Standard

Standard Test Method for Density and Relative Density (Specific Gravity) of Liquids by Lipkin Bicapillary Pycnometer¹

This standard is issued under the fixed designation D 941; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense to replace Method 402 of Test Method Standard No 791b. Consult the DoD Index of Specifications and Standards for the specific year of issue which has been adopted by the Department of Defense.

1. Scope

1.1 This test method covers the measurement of the density of any hydrocarbon material that can be handled in a normal fashion as a liquid at the specified test temperatures of 20 to 25°C. Its application is restricted to liquids having vapor pressures less than 80 kPa (600 mm Hg) and having viscosities less than 15 mm²/s (cst) at 20°C.

1.2 Two procedures are covered as follows:

1.2.1 *Procedure A*, for pure compounds and mixtures which are not highly volatile.

1.2.2 *Procedure B*, for highly volatile mixtures.

1.3 This test method provides a calculation procedure for converting density to relative density.

1.4 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Notes 1, 2, 6 and Annex A1.

2. Referenced Documents

2.1 *ASTM Standards:*

D 1250 Petroleum Measurement Tables²

E 1 Specification for ASTM Thermometers³

3. Terminology

3.1 *density*—mass per unit volume.

3.1.1 *Discussion*—In this test method, the measurement is at any given temperature and the units are grams per millilitre.

3.1.2 *relative density*—the ratio of the density of a material at a stated temperature to the density of water at a stated temperature.

4. Summary of Test Method⁴

4.1 The liquid sample is drawn into the pycnometer and weighed. It is then equilibrated at the test temperature, and the positions of the liquid levels are observed. The density or relative density of the sample is then calculated from its weight, a calibration factor proportional to an equal volume of water, and a term that corrects for the buoyancy of air.

5. Significance and Use

5.1 Density is a fundamental physical property which can be used in conjunction with other properties to characterize both the light and heavy fractions of petroleum and to assess the quality of crude oils.

5.2 Determination of the density or relative density of petroleum and its products is necessary for the conversion of measured volumes to volumes at the standard temperatures of 15°C or 60°F.

6. Apparatus

6.1 *Pycnometer*—A pycnometer conforming to the dimensions given in Fig. 1, constructed of borosilicate glass, and having a total weight not exceeding 30 g.

6.2 *Constant-Temperature Bath*—A water bath having a depth of at least 12 in. (305 mm), provided with means for maintaining a temperature of 20 ± 0.02°C or 25 ± 0.02°C.

6.3 *Bath Thermometer*—No suitable ASTM Celsius thermometers are available; ASTM Kinematic Viscosity Thermometers 44F and 45F designed for tests at 68°F (20°C) and 77°F (25°C) and conforming to the requirements prescribed in Specification E 1 are therefore specified. Ice point and bore corrections must be known to the nearest 0.02°F. In use, the thermometers must be immersed to a point at least 2°F above the test temperature.

6.4 *Pycnometer Holder*—Figure 2 shows the structural details of the holder proper. It can be made of brass or any other available metal that can be hard- or soft-soldered and that will not corrode in the thermostat liquid. Figure 3 illustrates a convenient mounting for suspending the holders in the thermostat. It consists of a brass bar 1/8 in. (3.2 mm) in thickness by 1 in. (25 mm) in width, of a length suitable for

¹ This test method is under the jurisdiction of ASTM Committee D-2 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.04 on Hydrocarbon Analysis.

Current edition approved Oct 31, 1988. Published December 1988. Originally published as D 941 - 47. Last previous edition D 941 - 83.

² *Annual Book of ASTM Standards*, Vol 05.01.

³ *Annual Book of ASTM Standards*, Vols 05.03 and 14.01.

⁴ For a more complete discussion of this method, see Davidson, J. A., Harvey, T., Kurtz, S. S., Jr., Lipkin, M. R., "Pycnometer for Volatile Liquids," *Industrial and Engineering Chemistry*, Analytical Edition, IENAA Vol 16, No. 1, 1944, p. 55 and H. M. Smith, and Cooperators, "Measurement of Density of Hydrocarbon Liquids by the Pycnometer," *Analytical Chemistry*, ANCHA Vol 22, Nov. 1952, p. 1452.