



Standard Test Methods for Rubber Properties in Compression or Shear (Mechanical Oscillograph)¹

This standard is issued under the fixed designation D945; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 These test methods cover the use of the Yerzley mechanical oscillograph for measuring mechanical properties of rubber vulcanizates in the generally small range of deformation that characterizes many technical applications. These properties include resilience, dynamic modulus, static modulus, kinetic energy, creep, and set under a given force. Measurements in compression and shear are described.^{2,3}

1.2 The test is applicable primarily, but not exclusively, to materials having static moduli at the test temperature such that forces below 2 MPa (280 psi) in compression or 1 MPa (140 psi) in shear will produce 20 % deformation, and having resilience such that at least three complete cycles are produced when obtaining the damped oscillatory curve. The range may be extended, however, by use of supplementary masses and refined methods of analysis. Materials may be compared either under comparable mean stress or mean strain conditions.

1.3 Computerized data acquisition systems and data evaluation methods for Yerzley Mechanical Oscillograph are included. The mechanical portion of the oscillograph remains the same. In the computerized type (digital data acquisition and recording), the mechanical recording mechanism has been replaced with a displacement transducer and digital data acquisition system, by which the required calculations are such that the results are available immediately and recorded in real time.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

¹ These test methods are under the jurisdiction of ASTM Committee D11 on Rubber and are the direct responsibility of Subcommittee D11.10 on Physical Testing.

Current edition approved July 1, 2016. Published July 2016. Originally approved in 1948. Last previous edition approved in 2012 as D945 – 06 (2012). DOI: 10.1520/D0945-16.

² A survey of some aspects of hysteresis and modulus in dynamic performance of polymers is available in a paper by Payne, A. R., "The Role of Hysteresis in Polymers," *Rubber Journal*, January 1964, p. 36.

³ One method of correlating fundamental data from the Yerzley oscillograph with dynamic tests at constant amplitude is described by Baldwin, F. P., in his paper, "Determination of the Dynamic Properties of Rubberlike Materials by Means of a Modified Yerzley Oscillograph," *The Rubber Age*, April 1950.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific warning see 12.14.

2. Referenced Documents

2.1 ASTM Standards:⁴

D832 Practice for Rubber Conditioning For Low Temperature Testing

D1207 Recommended Practice for Classifying Elastomeric Compounds for Resilient Automotive Mountings (Withdrawn 1971)⁵

D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries

2.2 SAE Standard:

SAE J16 Classification of Elastomer Compounds for Automotive Resilient Mountings^{6,7}

3. Terminology

3.1 Descriptions of Terms Specific to This Standard:

3.2 *effective dynamic modulus*—calculated from the formula for simple harmonic motion in a damped free oscillation. It is a composite index which includes the effect of such diverse factors as nonlinearity of stress-strain, changing molecular energies, and heat losses.

3.3 *point modulus*—ratio of total stress (force/area) to total strain (change in dimension/unstressed dimension) at one point

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁵ The last approved version of this historical standard is referenced on www.astm.org.

⁶ Available from Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096.

⁷ The Yerzley oscillograph was originally described in detail in the paper by Yerzley, F. L., "A Mechanical Oscillograph for Routine Tests of Rubber and Rubber-Like Materials," *Proceedings, ASTM*, Vol 39, 1939, p. 1180; also *Rubber Chemistry and Technology*, Vol XIII, No. 1, January 1940, p. 149.