This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

Designation: D1440 – 07 (Reapproved 2019)

Standard Test Method for Length and Length Distribution of Cotton Fibers (Array Method)[1]

This standard is issued under the fixed designation D1440; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the fiber length and length distribution in loose cotton fibers.

NOTE 1—For another method for measuring fiber length, see Test Method D1447.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*[2]

D123 Terminology Relating to Textiles
D1441 Practice for Sampling Cotton Fibers for Testing
D1447 Test Method for Length and Length Uniformity of Cotton Fibers by Photoelectric Measurement
D1776 Practice for Conditioning and Testing Textiles
D7139 Terminology for Cotton Fibers

3. Terminology

3.1 For all terminology related to D13.11, Cotton Fibers, see Terminology D7139.

3.1.1 The following terms are relevant to this standard: coefficient of variation, length group, length interval, mean length, pull, upper quartile length.

3.2 For all other terminology related to textiles see Terminology D123.

4. Summary of Test Method

4.1 A sorting apparatus consisting of two banks of parallel combs is used to straighten and align the fibers in a 75-mg test specimen. The fibers are pulled from one bank of combs and transferred to the other in such a manner that one end of each fiber is aligned with the base comb. The transfer is repeated to straighten the other ends of the fibers. As the fibers are withdrawn from the combs for the third time, they are placed in order of length on velvet covered boards. The pulls are measured, and those that fall within each length interval are collected and weighed. From these weight-length data, the upper quartile length, mean length, and coefficient of length variation are calculated.

5. Significance and Use

5.1 The array method provides objective measurements for determining the fiber length and length distribution in a sample of cotton. The results can be plotted to show the length-weight distribution of all the fibers in the sample. Data obtained from array tests are useful in fiber length research studies, for investigation of changes in fiber length distribution in ginning and mill processing, and for other research purposes.

5.2 Upper quartile length is correlated with, but usually longer than, Fibrograph and 2.5 % span length as defined in Test Method D1447. Judgment must be used in making comparisons between length measures from arrays and measures obtained by other methods, which may be basically different.

5.3 The coefficient of length variation is a measure of length distribution, or nonuniformity of length. Because the fiber weight-length distribution is usually highly skewed, statistical judgments based on the assumption of normality are not justified.

5.4 The array method makes a physical separation of fibers of different lengths. It therefore serves as a standard, or benchmark, with which other methods may be compared and by which their precision and accuracy may be judged.

[1] This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.11 on Cotton Fibers.

Current edition approved July 1, 2019. Published July 2019. Originally approved in 1955. Last previous edition approved in 2012 as D1440 – 07 (2012). DOI: 10.1520/D1440-07R19.

[2] For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States