



Designation: D1666 – 17

Standard Test Methods for Conducting Machining Tests of Wood and Wood-Base Panel Materials¹

This standard is issued under the fixed designation D1666; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

One of the significant characteristics of wood and wood-base panels is the facility with which they can be machined and fabricated. Different species and products, however, vary greatly in their behavior under cutting tools, so that some systematic method is needed for determining their suitability for uses where the character of the machined surface is of prime importance. Such uses include cabinetwork, millwork, and other applications where favorable machining properties are essential to good finish. For such products as common boards, on the other hand, good machining properties are secondary, although still an asset.

The machining test procedures presented in these test methods cover such common operations as planing, routing/shaping, turning, boring, mortising, and sanding. They are the result of many years of extensive research and development and include practical methods for qualitatively evaluating and interpreting the results. Because of their satisfactory use with a wide range of materials, it is believed that the methods are equally applicable to species, hardwoods and softwoods, and to wood-base panel materials, such as plywood, particleboard, fiberboard, and hardboard.

1. Scope

1.1 These test methods cover procedures for planing, routing/shaping, turning, mortising, boring, and sanding, all of which are common wood-working operations used in the manufacture of wood products. These tests apply, in different degrees, to two general classes of materials:

1.1.1 Wood in the form of lumber, and

1.1.2 Wood-base panel materials such as plywood and wood-base fiber and particle panels.

1.2 Because of the importance of planing, some of the variables that affect the results of this operation are explored with a view to determining optimum conditions. In most of the other tests, however, it is necessary to limit the work to one set of fairly typical commercial conditions in which all the different woods are treated alike.

1.3 Several factors enter into any complete appraisal of the machining properties of a given wood or wood-base panel. Quality of finished surface is recommended as the basis for evaluation of machining properties. Rate of dulling of cutting

tools and power consumed in cutting are also important considerations but are beyond the scope of these test methods.

1.4 Although the methods presented include the results of progressive developments in the evaluation of machining properties, further improvements may be anticipated. For example, by present procedures, quality of the finished surface is evaluated by visual inspection, but as new mechanical or physical techniques become available that will afford improved precision of evaluation, they should be employed.

1.5 The values stated in inch-pound units are to be regarded as the standard. The metric equivalents of inch-pound units may be approximate.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:

¹ These test methods are under the jurisdiction of ASTM Committee D07 on Wood and are the direct responsibility of Subcommittee D07.01 on Fundamental Test Methods and Properties.

Current edition approved March 1, 2017. Published June 2017. Originally approved in 1959. Last previous edition approved in 2011 as D1666 – 11. DOI: 10.1520/D1666-17.