



Standard Test Method for Tensile-Impact Energy to Break Plastics and Electrical Insulating Materials¹

This standard is issued under the fixed designation D 1822; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 This test method covers the determination of the energy required to rupture standard tension-impact specimens of plastic or electrical insulating materials. Materials that can be tested by this test method are those too flexible or too thin to be tested in accordance with Test Methods D 256, as well as more rigid materials.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

NOTE 1—This test method is not equivalent to ISO 8256, and results cannot be directly compared between the two methods.

1.3 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 256 Test Methods for Impact Resistance of Plastics and Electrical Insulating Materials²
- D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing²
- D 638 Test Method for Tensile Properties of Plastics²
- D 883 Terminology Relating to Plastics²
- D 1898 Practice for Sampling of Plastics²
- D 4000 Classification System for Specifying Plastic Materials³
- D 4066 Specification for Nylon Injection and Extrusion Materials³
- E 23 Test Methods for Notched Bar Impact Testing of Metallic Materials⁴

¹ This test method is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.10 on Mechanical Properties. Current edition approved April 10, 1999. Published July 1999. Originally published as D 1822 – 61 T. Last previous edition D 1822 – 93.

² Annual Book of ASTM Standards, Vol 08.01.

³ Annual Book of ASTM Standards, Vol 08.02.

⁴ Annual Book of ASTM Standards, Vol 03.01.

3. Terminology

3.1 *Definitions*—Definitions of terms applying to this test method appear in Terminology D 883.

4. Summary of Test Method

4.1 The energy utilized in this test method is delivered by a single swing of a calibrated pendulum of a standardized tension-impact machine. The energy to fracture by shock in tension is determined by the kinetic energy extracted from the pendulum of an impact machine in the process of breaking the specimen. One end of the specimen is mounted in the pendulum. The other end of the specimen is gripped by a crosshead which travels with the pendulum until the instant of impact and instant of maximum pendulum kinetic energy, when the crosshead is arrested.

5. Significance and Use

5.1 Tensile-impact energy is the energy required to break a standard tension-impact specimen in tension by a single swing of a standard calibrated pendulum under a set of standard conditions (Note 2). In order to compensate for the minor differences in cross-sectional area of the specimens as they will occur in the preparation of the specimens, the energy to break can be normalized to units of kilojoules per square metre (or foot-pounds-force per square inch) of minimum cross-sectional area. An alternative approach to normalizing the impact energy that compensates for these minor differences and still retains the test unit as joules (foot-pounds) is shown in Section 11. For a perfectly elastic material the impact energy might be reported per unit volume of material undergoing deformation. However, since much of the energy to break the plastic materials for which this test method is written is dissipated in drawing of only a portion of the test region, such normalization on a volume basis is not feasible. The test method permits two specimen geometries so that the effect of elongation or rate of extension, or both, upon the result can be observed. With the Type S (short) specimen the extension is comparatively low, while with the Type L (long) specimen the extension is comparatively high. In general, the Type S specimen (with its

*A Summary of Changes section appears at the end of this standard.

