



Standard Specification for Cutback Asphalt (Medium-Curing Type)¹

This standard is issued under the fixed designation D 2027; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers cutback petroleum asphalts of the medium-curing type for use in the construction and treatment of pavements.

2. Referenced Documents

2.1 ASTM Standards:²

- D 5 Test Method for Penetration of Bituminous Materials
- D 95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation
- D 113 Test Method for Ductility of Bituminous Materials
- D 140 Practice for Sampling Bituminous Materials
- D 402 Test Method for Distillation of Cut-Back Asphaltic (Bituminous) Products
- D 2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.40 on Asphalt Specifications.

Current edition approved March 1, 2004. Published March 2004. Originally approved in 1963. Last previous edition approved in 1997 as D 2027–97.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 2170 Test Method for Kinematic Viscosity of Asphalts (Bitumens)

D 3143 Test Method for Flash Point of Cutback Asphalt with Tag Open-Cup Apparatus

3. Properties

3.1 The cutback asphalt shall not foam when heated to application temperature and shall conform to the requirements prescribed in Table 1.

4. Test Methods

4.1 The materials shall be sampled in accordance with Practice D 140, and the properties enumerated in this specification shall be determined in accordance with the following ASTM test methods:

- 4.1.1 *Flash Point (Tag Open-Cup)*—Test Method D 3143.
- 4.1.2 *Viscosity, Kinematic*—Test Method D 2170.
- 4.1.3 *Distillation*—Test Method D 402.

NOTE 1—If a 100-mL graduate does not permit sufficiently close readings to determine conformity to this specification with the desired accuracy, receivers graduated with 0.1-mL divisions shall be used.

- 4.1.4 *Penetration*—Test Method D 5.
- 4.1.5 *Ductility*—Test Method D 113.
- 4.1.6 *Solubility in Trichloroethylene*—Test Method D 2042.
- 4.1.7 *Water*—Test Method D 95.

