



Designation: D2096 – 11 (Reapproved 2024)

Standard Test Method for Colorfastness and Transfer of Color in the Washing of Leather¹

This standard is issued under the fixed designation D2096; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the colorfastness of colored leathers, with or without a surface coating. The leathers to be tested are of the type normally expected to withstand frequent laundering. This test method also covers the simultaneous staining of adjacent textile materials when the leather specimens are washed. This test method does not apply to wet blue. Two procedures are covered depending on the apparatus used:

1.1.1 *Procedure A*, using the Launder-Ometer,² and

1.1.2 *Procedure B*, using an alternative washing machine.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values stated in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.04 on Apparel. This test method was developed in cooperation with the American Leather Chemists Assn.

Current edition approved Dec. 1, 2024. Published December 2024. Originally approved in 1962. Last previous edition approved in 2019 as D2096 – 11 (2019) ^{ϵ 1}. DOI: 10.1520/D2096-11R24.

² The Launder-Ometer and its development are described in the *American Dyestuff Reporter*, Oct. 29, 1928, p. 679. It is described also in the current *Technical Manual of the American Association of Textile Chemists and Colorists*. Such an apparatus is illustrated in Figs. 3, 4, and 5.

The sole source of supply of the apparatus known to the committee at this time is SDL Atlas, 3934 Airway Drive, Rock Hill SC 29732. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.

2. Referenced Documents

2.1 *ASTM Standards*:³

D499 Specification for White Floating Toilet Soap (Withdrawn 2000)⁴

2.2 *ISO Standard*:⁵

ISO R105/I, Part 2 Gray Scale for Evaluating Change in Color

ISO R105/I, Part 3 Gray Scale for Evaluating Staining

2.3 *ASTM Adjunct*:⁶

Leather washing apparatus (1 drawing)

3. Summary of Test Method

3.1 Three leather specimens 50 mm by 80 mm (approximately 2 in. by 3 in.), and one piece of multifiber test fabric of nearly equal size are washed together in soapy water at 120 °F (49 °C). After ½ h of washing, the leather specimens and cloth are removed and rinsed carefully in running water at about 95 °F (35 °C). One leather specimen and the test cloth are removed and air-dried. A new piece of test cloth is added to the remaining two leather specimens and these are washed, as above, for ½ h. The rinsing is repeated; again one leather specimen and the test cloth are removed for drying. The remaining leather specimen, with a new piece of test cloth, is washed again for ½ h. This final leather specimen and test cloth are then rinsed and dried as above. When dry, the color of the washed leather specimens is rated by comparing it with an unwashed piece of leather. Transfer of color to the test fabric is rated by comparison with an unwashed piece of test fabric. These comparisons are made with the aid of the proper Gray Scale. All ratings are made on dry test specimens.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁶ Detailed drawings for such an apparatus are available in a digital PDF file from ASTM International Headquarters. Order Adjunct ADJD2096-E-PDF. Original adjunct produced in 1962. Adjunct last updated in 2020.