



Standard Test Method for Stain Removal From Multicolor Lacquers¹

This standard is issued under the fixed designation D 2198; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (€) indicates an editorial change since the last revision or reapproval.

€¹ NOTE—Unit of measurement statement was added editorially in June 1996.

1. Scope

1.1 This test method covers a procedure for the removal of pencil, crayon, and grease stains from multicolor lacquer films that have been applied to primed steel panels.

NOTE 1—Due to the nature of the test, comparable results can be obtained only when exactly the same materials and apparatus are used. In this test method it has not been found possible to describe the materials and apparatus adequately in more than general terms.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

A 109 Specification for Steel, Strip, Carbon, Cold-Rolled²
A 366/A366M Specification for Steel, Sheet, Carbon, Cold-Rolled, Commercial Quality²

D 209 Specification for Lampblack Pigment³

D 609 Practice for Preparation of Steel Panels for Testing Paint, Varnish, Lacquer, and Related Products⁴

2.2 U. S. Federal Specifications:⁵

Fed. Spec. EE-0-451C Specification for Oleo (Margarine)

Fed. Spec. TTV-121C Specification for Varnish, Spar, Water Resisting

Fed. Spec. VV-0-551 Specification for Oil, Lubricating, Marine and Engine, Mineral

Fed. Spec. VV-P-236 Specification for Petrolatum

2.3 U. S. Military Specification:⁵

MIL-P-11414A Specification for Primer Coating, Lacquer, Rust Inhibiting

3. Summary of Test Method

3.1 Three 6½ by 17-in. (165 by 430 mm) primed steel panels are sprayed with multicolor lacquer and allowed to dry for 24 h. Varnish is then applied to the ends of the panels and allowed to dry 72 h. The three stains are applied by a mechanical apparatus and removed by washing.

4. Significance and Use

4.1 The procedure described in this test method is intended as an aid in evaluating the ease of removal for surface stains encountered by surfaces coated with multicolor lacquers.

5. Apparatus and Materials

5.1 *Steel Panels*, 6½ by 17 in. (165 by 430 mm), 20-gage cold-rolled steel conforming to Specification A 109 or Specification A 366/A 366M.

5.2 *Washability Machine*.⁶

5.3 *Lacquer Primer*, conforming to MIL-P-11414A.

5.4 *Drafting Pencil*.

5.5 *China Marking Crayon*.

5.6 *Wetting Agent*.⁷

5.7 *Amorphous Silica*.

5.8 *Diaper Cloth*.

5.9 *Varnish*, clear and waterproof, conforming to Fed. Spec. TT-V-121C or equal cut in mineral spirits.

5.10 *Carriage*, for mounting pencil and crayon.

5.11 *Arm*, extendible, for mounting mohair roller.

5.12 *Mohair Roller*, 1½ in. (40 mm), for application of grease stain.

5.13 *Glass Plate*, 4 by 7 in. (100 by 175 mm), for holding grease stain.

5.14 *Grease*—The grease shall consist of the following ingredients:

5.14.1 *Lanolin*, anhydrous, 50 g,

5.14.2 *Petrolatum*, 50 g, conforming to Fed. Spec. VV-P-236,

¹ This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.55 on Factory-Applied Coatings on Preformed Products.

Current edition approved Aug. 31, 1984. Published January 1985. Originally published as D 2198 – 63 T. Last previous edition D 2198 – 68 (1979)€¹.

² *Annual Book of ASTM Standards*, Vol 01.03.

³ *Annual Book of ASTM Standards*, Vol 06.03.

⁴ *Annual Book of ASTM Standards*, Vol 06.01.

⁵ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁶ Gardner Model AG8100, available from Byk-Gardner, Inc., Gardner Laboratory, 2435 Linden Ln., Silver Spring, MD 20910, has been found suitable for this purpose.

⁷ Triton X-100, available from Rohm and Haas Marketing Services, Independence Mall West, Philadelphia, PA 19105, has been found suitable for this purpose.