



Standard Test Method for Tensile Properties of Glass Fiber Strands, Yarns, and Rovings Used in Reinforced Plastics¹

This standard is issued under the fixed designation D2343; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of the comparative tensile properties of glass fiber strands, yarns, and rovings in the form of impregnated rod test specimens when tested under defined conditions of pretreatment, temperature, humidity, and tension testing machine speed. This test method is applicable to continuous filament, glass fiber materials that have been coated with a resin compatible sizing. This method is intended for use in quality control and R & D, and should not be used to develop composites design data.

NOTE 1—This method is technically equivalent to the short method described in ISO 9163.

NOTE 2—Prime consideration should be given to the use of a polymeric binder that produces specimens that yield the highest consistent values for the glass fiber material under test. Tensile properties may vary with specimen preparation, resin impregnation system, and speed and environment of testing. Consequently, where precise comparative results are desired, these factors must be carefully controlled.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

NOTE 3—Prime consideration should be given to the use of a polymeric binder that produces specimens that yield the highest consistent values for the glass fiber material under test. Tensile properties may vary with specimen preparation, resin impregnation system, and speed and environment of testing. Consequently, where precise comparative results are desired, these factors must be carefully controlled.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.18 on Reinforced Thermosetting Plastics.

Current edition approved Sept. 1, 2009. Published September 2009. Originally approved in 1965. Last previous edition approved in 2008 as D2343 - 08. DOI: 10.1520/D2343-09.

2. Referenced Documents

2.1 ASTM Standards:²

D618 Practice for Conditioning Plastics for Testing

D883 Terminology Relating to Plastics

D3039/D3039M Test Method for Tensile Properties of Polymer Matrix Composite Materials

D5083 Test Method for Tensile Properties of Reinforced Thermosetting Plastics Using Straight-Sided Specimens

E4 Practices for Force Verification of Testing Machines

E6 Terminology Relating to Methods of Mechanical Testing

2.2 ISO Standard:

ISO 9163 Textile Glass—Rovings—Manufacture of Test Specimens and Determination of Tensile Strength of Impregnated Rovings

3. Terminology

3.1 Definitions:

3.1.1 Definitions of terms and symbols relating to this test method appear in Terminologies E6 and D883.

4. Summary of Test Method

4.1 This test method consists of impregnating glass fiber strands, yarns, or rovings with a suitable polymeric binder material and loading the resulting test specimens to failure in a tension testing machine having a constant-rate-of crosshead movement. The cross sectional area is determined from skeins of glass fiber taken before and after each set of test specimens. After impregnation and curing, the specimens shall either be tabbed using glass fiber mat or cardboard and tested with standard grips; or the ends shall be sanded with 240 grit sandpaper or fine emery cloth and tested using rubber faced grips.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.