



Designation: D 2417 – 77 (Reapproved 1981)

Standard Specification for PERFORATED, LAMINATED-WALL BITUMINIZED FIBER PIPE FOR GENERAL DRAINAGE¹

This standard is issued under the fixed designation D 2417; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This specification has been approved for use by agencies of the Department of Defense to replace Federal Specification SS-P-1540B, Type II, Class 2, Style A and for listing in the DoD Index of Specifications and Standards.

1. Scope

1.1 This specification covers laminated-wall bituminized fiber perforated drainage pipe for use in agricultural, land, and general drainage.

NOTE—The values stated in SI units are to be regarded as the standard.

2. Applicable Documents

2.1 ASTM Standard:

D 2315 Methods of Testing Laminated-Wall Bituminized Fiber Pipe²

3. Materials and Manufacture

3.1 *Pipe and Couplings*—Pipe and couplings shall be composed of a multi-ply laminated convolute or spiral fibrous structure, with the laminations being adhered with a heat- and water-resistant adhesive and then thoroughly impregnated with a bituminous compound. The pipe shall have a smooth interior surface free of obstructions and rough or flaky areas. Bends, fittings and adapters shall be of the same material as the pipe, or of a material having equal or better physical and chemical properties.

3.2 *Joint Systems*—Pipe and fittings shall use either of the following joint systems:

3.2.1 *Type TJ Joints*—Pipe and fittings shall be provided with accurately machined or molded tapered joints, and a taper-sleeve coupling shall be provided for each length of pipe and for each fitting where applicable. The slope of the taper in both pipe and coupling shall be 2 deg (4 deg including angle) (see Fig. 1).

3.2.2 *Type BJ Joints*—Pipe and fittings

shall have squarely cut ends, and a split-collar coupling shall be provided for each length of pipe and for each fitting where applicable (see Fig. 2).

4. Physical and Chemical Requirements

4.1 *Resistance to Flattening*—The requirements for resistance to flattening shall be that the decrease in diameter shall not exceed 3 %, when loaded with 1460 N/m (100 lbf/ft).

4.2 *Crushing Strengths*—The pipe shall have a minimum three-edge-bearing crushing strength of 13.1 kN/m (900 lbf/ft) (wet and dry).

4.3 *Water Absorption*—The maximum water absorption shall be 2 % of the original weight.

4.4 *Boiling Water Resistance*—Specimens shall exhibit not less than 90 % of the crushing strength.

4.5 *Heat Resistance*—The heat shall not cause a weight loss over 1 % in the specimen due to the exudation of the impregnant.

4.6 *Chemical Resistance*—Specimens shall show no visible sign of chemical reaction or deterioration of the impregnant.

4.7 *Kerosine Resistance*—Specimens shall meet the crushing strength requirements.

5. Dimensions

5.1 *Pipe and Couplings*—The dimensions

¹ This specification is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.16 on Bituminized Fiber Pipe.

Current edition approved Sept. 30, 1977. Published November 1977. Originally published as D 2417 – 65 T. Last previous edition D 2417 – 73.

² *Annual Book of ASTM Standards*, Vol 04.04.

