



Designation: D2512 – 17

Standard Test Method for Compatibility of Materials with Liquid Oxygen (Impact Sensitivity Threshold and Pass-Fail Techniques)¹

This standard is issued under the fixed designation D2512; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This method^{2,3,4} covers the determination of compatibility and relative sensitivity of materials with liquid oxygen under impact energy using the Army Ballistic Missile Agency (ABMA)-type impact tester. Materials that are impact-sensitive with liquid oxygen are generally also sensitive to reaction by other forms of energy in the presence of oxygen.

1.2 *This standard should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use.*

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee G04 on Compatibility and Sensitivity of Materials in Oxygen Enriched Atmospheres and is the direct responsibility of Subcommittee G04.01 on Test Methods.

Current edition approved July 1, 2017. Published July 2017. Originally approved in 1966. Last previous edition approved in 2002 as D2512 – 95 (2002)^{ε1} which was withdrawn January 2017 and reinstated in July 2017. DOI: 10.1520/D2512-17.

² NASA Handbook 8060. 1B, Ambient LOX Mechanical Impact Screening Test, September 1981, pp. 4-53 through 4-71. "Oxygen Systems." George C. Marshall Space Flight Center, National Aeronautics and Space Administration. Specification MSFC 106B. September 1981.

³ "Lubrication and Related Research and Test Method Development for Aviation Propulsion Systems." Technical Report No. 59-726. Wright Air Development Division, January 1960.

⁴ "General Safety Precautions for Missile Liquid Propellants."

2. Referenced Documents

2.1 ASTM Standards:⁵

C145 Specification for Solid Load-Bearing Concrete Masonry Units (Withdrawn 1992)⁶

D1193 Specification for Reagent Water

2.2 Military Standards:

MIL-D-16791G Detergent, General Purpose (Liquid, Non-ionic)⁷

MIL-P-27401C Propellant Pressurizing Agent, Nitrogen⁷

MIL-PRF-25508F Propellant, Oxygen⁷

MIL-T-27602B Trichloroethylene, Oxygen Propellant Compatible⁸

MIL-C-81302D Cleaning Compound, Solvent, Trichlorotrifluorocarbon⁷

2.3 ASTM Adjuncts:

Type Impact Tester and Anvil Region Assembly, 38 Drawings

3. Summary of Test Method

3.1 A sample of the test material is placed in a specimen cup, precooled and covered with liquid oxygen, and placed in the cup holder located in the anvil region assembly of the impact tester. A precooled striker pin is then centered in the cup. The plummet is dropped from selected heights onto the pin, which transmits the energy to the test specimen. Observation for any reaction is made and the liquid oxygen impact sensitivity of the test material is noted. Drop tests are continued using a fresh specimen cup and striker pin for each drop, until

⁵ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁶ The last approved version of this historical standard is referenced on www.astm.org.

⁷ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁸ Cancelled in 1983. Previously available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.