



Standard Tolerances for Yarns Spun on the Woolen System¹

This standard is issued under the fixed designation D 2644; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These tolerances are applicable to all yarns spun on the woolen system and composed of any fiber or mixture of fibers, even though there might not be any wool present in the yarn.

NOTE 1—For tolerances for other spun yarns, see Tolerances D 2645 .

2. Referenced Documents

2.1 ASTM Standards:

D 123 Terminology Relating to Textiles²

D 1422 Test Method for Twist in Single Spun Yarns by the Untwist-Retwist Method²

D 1423 Test Method for Twist in Yarns by the Direct-Counting Method²

D 1578 Test Method for Breaking Strength of Yarn in Skein Form²

D 1907 Test Method for Linear Density of Yarn (Yarn Number) by the Skein Method²

D 2256 Test Method for Tensile Properties of Yarns by the Single-Strand Method²

D 2257 Test Method for Extractable Matter in Textiles²

D 2258 Practice for Sampling Yarn for Testing²

D 2494 Test Method for Commercial Mass of a Shipment of Yarn or Manufactured Staple Fiber or Tow²

D 2645 Tolerances for Yarns Spun on the Cotton or Worsted Systems²

D 3888 Terminology Related to Open-End Spinning³

D 3990 Terminology Relating to Fabric Defects³

D 4849 Terminology Relating to Fibers and Yarns³

3. Terminology

3.1 Definitions:

3.1.1 For definitions of textile terms used in these tolerances: woolen-spun and woolen system, refer to Terminology D 4849.

3.1.2 For definitions of terms used in this standard: tolerances and wool, refer to Terminology D 123.

3.1.3 For other textile terms used in this test method, refer to Terminology D 123, D 3888, D 3990, and D 4849.

4. Sampling

4.1 Take samples as directed in the applicable material specification, or as agreed upon by the purchaser and the supplier. In the absence of an applicable specification or other agreement, proceed as directed in Practice D 2258.

5. Tolerances

5.1 *Strength*—The average breaking force of each lot shall be equal to or greater than the specified minimum average.

5.2 *Yarn Number*—The average yarn number shall be within the following tolerances:

	Deviation from the Specified Yarn Number, %
500 tex or 0.6 woolen run to 165 tex or 1.86 woolen run	± 7.5
Finer than 165 tex or 1.86 woolen run	± 5.0

5.3 Twist:

5.3.1 The direction of twist in each package or end shall be S or Z, as specified.

5.3.2 The average twist shall conform to the limits: specified value ± 7.5 % of the specified value.

5.3.3 The average twist of the package containing the highest average twist shall not be higher than that of the package containing the lowest average twist by more than 15.0 % of the lower average.

5.4 *Extractable Matter*—The average percent extractable matter shall not exceed the following values:

	%
Dry-spun	2.0
Oil-spun, semi-scoured	15.0
Oil-spun scoured:	
Blends, 50 % wool or less	4.0
All wool or more than 50 % wool	10.0

5.5 *Commercial Mass*—In the absence of other contractual agreements, the invoice mass, that is the commercial mass as adopted in a specific branch of the textile trade and as determined by the supplier, shall not exceed the commercial mass as determined by the purchaser, by more than 1 %. In branches of the textile trade which use the net mass as the commercial mass, the latter is subject to the same limitation.

¹ These tolerances are under the jurisdiction of ASTM Committee D13 on Textiles, and are the direct responsibility of Subcommittee D13.58, Yarn Test Methods, General.

Current edition approved Sept. 10, 2002. Published November 2002. Originally published as D 2644 – 67 T. Last previous edition D 2644 – 81(1996)^{e1}.

² Annual Book of ASTM Standards, Vol 07.01.

³ Annual Book of ASTM Standards, Vol 07.02.