



Standard Test Method for Chipping Resistance of Coatings¹

This standard is issued under the fixed designation D 3170; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the resistance of coatings to chipping damage by stones or other flying objects.

NOTE 1—This test method is similar to SAE J-400.

1.2 The values stated in metric units are to be regarded as the standard. The English units given in parentheses are for information only. All dimensions are nominal unless otherwise specified.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products²

D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels²

D 1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers²

D 1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base²

D 1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base²

D 1733 Method of Preparation of Aluminum-Alloy Panels for Testing Paint, Varnish, Lacquer, and Related Products³

D 2201 Practice for Preparation of Zinc-Coated and Zinc-Alloy-Coated Steel Panels for Testing Paint and Related Products²

2.2 Other Documents:

Test for Chip Resistance of Surface Coatings (J-400)⁴

3. Summary of Test Method

3.1 Standardized road gravel is projected by means of a controlled air blast at the coated specimens. All testing is conducted under controlled temperature conditions, generally either at ambient (room) temperature or at $-29^{\circ}\text{C} \pm 3^{\circ}\text{C}$ ($-20^{\circ} \pm 5^{\circ}\text{F}$). After the gravel impact, tape is applied to remove any loose coating chips and the degree of chipping is determined.

4. Significance and Use

4.1 Owners consider chipping of coatings, particularly on the leading faces and edges of automobile surfaces, unacceptable. In formulating a coating or coating system to meet service requirements, the resistance to chipping damage by flying objects such as gravel is one of the properties of importance since it can vary considerably as other properties are adjusted. Since resistance to chipping decreases at lower temperatures partly as the result of decreased flexibility, the test may be more directly related to service conditions by performing it at a low temperature. This test method is designed to produce a controlled amount of impact by the media on the coated panel in order to enhance reproducibility.

5. Apparatus

5.1 *Gravel-Projecting Machine (Gravelometer)*, constructed according to the design specifications shown in Fig. 1.⁵ There are two types of Gravelometers: the old cabinet style and the newer, modular style with an electronic feed mechanism.

NOTE 2—It is recommended that the operation/maintenance checklist shown in Appendix X1 should be completed at least once per month for gravelometers that are operated on a weekly basis, and once every 6 months for gravelometers that are operated less frequently. Note that values in the checklist are specific to the standard gravel testing protocol.

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.55 on Factory Applied Coatings on Preformed Products.

Current edition approved July 10, 2003. Published September 2003. Originally approved in 1973. Last previous edition approved in 2001 as D 3170 - 01.

² *Annual Book of ASTM Standards*, Vol 06.01.

³ Discontinued, see 1980 *Annual Book of ASTM Standards*, Part 27.

⁴ Available from the Society of Automotive Engineers, 400 Commonwealth Dr., Warrendale, PA 15096.

⁵ The sole source of a suitable apparatus meeting these specifications known to the committee at this time is Q-Panel Co., 26200 First St., Westlake, OH 44135. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.