



Designation: D 3289 – 9703

Standard Test Method for Density of Semi-Solid and Solid Bituminous Materials (Nickel Crucible Method)¹

This standard is issued under the fixed designation D 3289; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

¹ This test method is under the jurisdiction of ASTM Committee D-4 D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.47 on Miscellaneous Asphalt Tests.

Current edition approved Aug. 10, 1997; 2003. Published April 1998; May 2003. Originally published as D 3289-74, approved in 1974. Last previous edition D 3289-85 (1990)^ε, approved in 1997 as D 3289-97.

1. Scope

1.1 This test method covers the determination of the density of semi-solid and solid bituminous materials by weighing in air and in water.

NOTE 1—An alternate method for determining the density of semi-solid and solid bituminous materials is Test Method D 70. For materials which are too fluid for use of this method, use Test Method D 3142.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are provided for information purposes only.

1.3—

1.2 This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials²

D 70 Test Method for Density of Semi-Solid and Solid Bituminous Materials (Pycnometer Method)³

D 140 Practice for Sampling Bituminous Materials³

D 3142 Test Method for Density of Liquid Asphalts (Hydrometer Method)³

D 4311 Practice for Determining Asphalt Volume Correction to a Base Temperature³

E 1 Specification for ASTM Thermometers⁴

3. Terminology

3.1 *density*—the mass per unit volume of a material.

3.2 *relative density*—the ratio of the mass of a given volume of a material to the mass of the same volume of water at the same temperature. (Note 2)

NOTE 2—Relative density is also called specific gravity.

4. Summary of Test Method

4.1 The sample is placed in a nickel crucible and weighed in air, and then in water at the test temperature. The density is calculated from the mass of the sample and its apparent mass when weighed in water.

5. Significance and Use

5.1 Values of density are used for converting volumes to units of mass, and for correcting measured volumes from the temperature of measurement to a standard temperature using Practice D 4311.

² Annual Book of ASTM Standards, Vol 04.02.

³ Annual Book of ASTM Standards, Vol 04.03.

⁴ Annual Book of ASTM Standards, Vol 14.03.