This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

Designation: D3616 – 95 (Reapproved 2019)

Standard Test Method for Rubber—Determination of Gel, Swelling Index, and Dilute Solution Viscosity[1]

This standard is issued under the fixed designation D3616; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the dilute solution viscosity (DSV), the gel characteristics, and the swelling index of raw non-oil-extended and non-pigmented SBR and NBR.

1.2 This test method may be used to determine the DSV and gel characteristics of rubbers other than SBR and NBR, however, solvents other than 2-butanone and toluene may be required.

1.3 This test method is not intended for the measurement of micro-gel.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*[2]

D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries

2.2 *Other Document:*[3]

"Reagent Chemicals, American Chemical Society Specifications"

3. Summary of Test Method

3.1 A weighed sample is allowed to stand 16 to 20 h in a suitable solvent. The sol, or soluble portion, is removed from the rubber mixture and the viscosity is determined on this solution.

3.2 A portion of the sol is used for the determination of the dissolved rubber. This is obtained by evaporation of the solvent.

3.3 The swelling index of the gel is determined by comparing the dry gel mass to the swollen gel mass.

4. Significance and Use

4.1 These tests are particularly useful for quality control in the production of synthetic rubbers.

4.2 Percent gel is a measure of the amount of insoluble rubber present in the chosen solvent. Gel may be introduced intentionally in some rubbers. Variations from a normal level indicate changes in the polymerization system.

4.3 Swelling index is a measure of the type of gel. Gel with a low-swelling index is referred to as "hard gel" and usually indicates the presence of material that does not break down readily by milling. A high-swelling index normally indicates the presence of a "loose gel" that may be broken down easily by milling.

4.4 In low-gel or gel-free rubbers, the DSV correlates directly with the molecular weight. Since the viscosity is measured only on the soluble portion of the rubber, the use of DSV to predict molecular weight in rubbers having high gel values is meaningless.

5. Apparatus

5.1 *Borosilicate Weighing Bottle,* 45/12 standard taper, 40 mm in inside diameter, 100 mm high, with cover.

[1] This test method is under the jurisdiction of ASTM Committee D11 on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee D11.11 on Chemical Analysis.

Current edition approved Jan. 1, 2019. Published January 2019. Originally approved in 1977. Last previous edition approved in 2014 as D3616 – 95 (2014). DOI: 10.1520/D3616-95R19.

[2] For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[3] Available from the American Chemical Society, 1155 Sixteenth Street, NW, Washington, DC, 20036.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States