



Standard Specification for Natural Red and Brown Iron Oxide Pigments¹

This standard is issued under the fixed designation D 3722; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers dry and wet ground naturally occurring iron oxide, dry and wet ground calcined naturally occurring iron oxide, and mixtures of these with synthetic iron oxides. These pigments are suitable for use in paints or coatings.

2. Referenced Documents

2.1 ASTM Standards:

D 50 Test Methods for Chemical Analysis of Yellow, Orange, Red, and Brown Pigments Containing Iron and Manganese²

D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints²

D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments²

D 387 Test Method for Color and Strength of Color Pigments with a Mechanical Muller³

D 1208 Test Methods for Common Properties of Certain Pigments²

3. Composition and Properties

3.1 The pigments shall conform to the following requirements:

Total iron as Fe ₂ O ₃ , min, %	70.0
Moisture and other volatile matter, max, %	1.0
Organic coloring matter	none
Total sulfates expressed as SO ₃	2.0

Matter soluble in water, max, %	2.0
Matter soluble in water, max, % (primer pigments)	1.0
Coarse particles (total residue retained on a No. 325 (45-μm) sieve) max, %	2.0

3.2 Inasmuch as iron oxide pigments are available in a range of colors, the mass color and, if desired by the purchaser, the character of the tint and the tinting strength shall be within mutually agreed upon limits of a reference sample acceptable to both the seller and the purchaser when tested in accordance with Test Method D 387.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear samples shall be taken from different packages in the ratio of two samples for each 5 tons (inch-pound or SI), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately, or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the appropriate ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.1.1 *Total Iron Oxide, Sulfur, and Organic Coloring Matter*—Test Methods D 50.

5.1.2 *Moisture and Other Volatile Matter*—Test Method D 280, Method A.

5.1.3 *Matter Soluble in Water*—Test Method D 1208.

5.1.4 *Coarse Particles in Dry Pigments*—Test Method D 185.

6. Keywords

6.1 iron oxide; natural brown; pigments

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D01.31 on Pigments Specifications.

Current edition approved Oct. 29, 1982. Published January 1983. Originally published as D 3722 – 78. Last previous edition D 3722 – 78.

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 06.01.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This document is now
POOBLIC