



Designation: D3839 – 14 (Reapproved 2019)

Standard Guide for Underground Installation of “Fiberglass” (Glass-Fiber Reinforced Thermosetting-Resin) Pipe¹

This standard is issued under the fixed designation D3839; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This practice establishes procedures for the burial of pressure and nonpressure “fiberglass” (glass-fiber-reinforced thermosetting-resin) pipe in many typically encountered soil conditions. Included are recommendations for trenching, placing pipe, joining pipe, placing and compacting backfill, and monitoring deflection levels. Guidance for installation of fiberglass pipe in subaqueous conditions is not included.

1.2 Product standards for fiberglass pipe encompass a wide range of product variables. Diameters range from 1 in. to 13 ft (25 mm to 4000 mm) and pipe stiffnesses range from 9 to over 72 psi (60 to 500 kPa) with internal pressure ratings up to several thousand pound force per square inch. This standard does not purport to consider all of the possible combinations of pipe, soil types, and natural ground conditions that may occur. The recommendations in this practice may need to be modified or expanded to meet the needs of some installation conditions. In particular, fiberglass pipe with diameters of a few inches are generally so stiff that they are frequently installed in accordance with different guidelines. Consult with the pipe manufacturer for guidance on which practices are applicable to these particular pipes.

1.3 The scope of this practice excludes product-performance criteria such as a minimum pipe stiffness, maximum service deflection, or long-term strength. Such parameters may be contained in product standards or design specifications, or both, for fiberglass pipe. It is incumbent upon the specified product manufacturer or project engineer to verify and ensure that the pipe specified for an intended application, when installed in accordance with procedures outlined in this practice, will provide a long-term, satisfactory performance in accordance with criteria established for that application.

NOTE 1—There is no known ISO equivalent to this standard.

NOTE 2—A discussion of the importance of deflection and a presenta-

tion of a simplified method to approximate field deflections are given in AWWA Manual of Practice M45 Fiberglass Pipe Design.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- D8 Terminology Relating to Materials for Roads and Pavements**
- D653 Terminology Relating to Soil, Rock, and Contained Fluids**
- D698 Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400 ft-lbf/ft³ (600 kN-m/m³))**
- D883 Terminology Relating to Plastics**
- D1556 Test Method for Density and Unit Weight of Soil in Place by Sand-Cone Method**
- D2167 Test Method for Density and Unit Weight of Soil in Place by the Rubber Balloon Method**
- D2216 Test Methods for Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass**
- D2487 Practice for Classification of Soils for Engineering Purposes (Unified Soil Classification System)**

¹ This practice is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping Systems and Chemical Equipment.

Current edition approved Aug. 1, 2019. Published August 2019. Originally approved in 1979. Last previous edition approved in 2014 as D3839 – 14. DOI: 10.1520/D3839-14R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**