



Standard Specification for Silicone Fluid Used for Electrical Insulation¹

This standard is issued under the fixed designation D 4652; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers silicone fluid for use in transformers, capacitors, and electronic assemblies as an insulating or cooling medium, or both.

1.2 Silicone fluid covered by this specification is polydimethylsiloxane having a nominal viscosity of 50 cSt at 25°C and a fire point of 340°C or greater. This specification applies only to new silicone fluid. Information on in-service maintenance testing is available in appropriate guides.²

2. Referenced Documents

2.1 ASTM Standards:

- D 92 Test Method for Flash and Fire Points by Cleveland Open Cup³
- D 97 Test Method for Pour Point of Petroleum Products³
- D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)³
- D 664 Test Method for Acid Number of Petroleum Products by Potentiometric Titration³
- D 877 Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using Disk Electrodes⁴
- D 923 Test Method for Sampling Electrical Insulating Liquids⁴
- D 924 Test Method for Dissipation Factor (or Power Factor) and Relative Permittivity (Dielectric Constant) of Electrical Insulating Liquids⁴
- D 974 Test Method for Acid and Base Number by Color-Indicator Titration³
- D 1169 Test Method for Specific Resistance (Resistivity) of Electrical Insulating Liquids⁴
- D 1298 Practice for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method³

¹ This specification is under the jurisdiction of ASTM Committee D-27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.02 on Synthetics.

Current edition approved Aug. 15, 1992. Published October 1992. Last previous edition D 4652 – 87.

² IEEE C57.111, IEEE Guide for Acceptance of Silicone Insulating Fluid and its Maintenance in Transformers is published by the Insulating Fluids Subcommittee of the IEEE Power Engineering Society Transformers Committee.

³ Annual Book of ASTM Standards, Vol 05.01.

⁴ Annual Book of ASTM Standards, Vol 10.03.

- D 1481 Test Method for Density and Relative Density (Specific Gravity) of Viscous Materials by Lipkin Bicapillary Pycnometer³
- D 1533 Test Methods for Water in Insulating Liquids (Karl Fischer Reaction Method)⁴
- D 1807 Test Methods for Refractive Index and Specific Optical Dispersion of Electrical Insulating Liquids⁴
- D 2129 Test Method for Color of Water White Electrical Insulating Liquids⁴
- D 2161 Practice for Conversion of Kinematic Viscosity to Saybolt Universal Viscosity or to Saybolt Furol Viscosity⁵
- D 2225 Methods of Testing Silicone Fluids Used for Electrical Insulation⁴
- D 2864 Terminology Relating to Electrical Insulating Liquids and Gases⁴
- D 4052 Test Method for Density and Relative Density of Liquids by Digital Density Meter⁶
- D 4059 Test Method for Analysis of Polychlorinated Biphenyls in Insulating Liquids by Gas Chromatography⁴
- D 4559 Test Method for Volatile Matter in Silicone Fluid⁴

3. Terminology

3.1 Definitions and descriptions of terms specific to this specification are given in Methods D 2225 and Terminology D 2864.

4. Sampling and Testing

- 4.1 Take all samples in accordance with Methods D 923.
- 4.2 Test in accordance with the methods specified in Table 1.

NOTE 1—Because of the different needs of the various users, items relating to packaging, labeling, and quality assurance are subject to buyer-seller agreement.

NOTE 2—In addition to all other tests listed herein, it is sound engineering practice for the apparatus manufacturer to perform a functional evaluation of silicone fluid in insulation systems, prototype structures, or full-scale apparatus, or any combination thereof, to assure suitable service life.

5. Detail Requirements

- 5.1 The silicone fluid, as received, shall conform to the

⁵ Annual Book of ASTM Standards, Vol 05.01.

⁶ Annual Book of ASTM Standards, Vol 05.02.

