



Standard Test Method for Determination of Quinoline Insolubles (QI) in Tar and Pitch by Pressure Filtration¹

This standard is issued under the fixed designation D4746; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial changes were made throughout the test method in September 2014.

1. Scope*

1.1 This test method covers the determination of the quinoline-insoluble matter (QI) in tar and pitch by pressure filtration and gives results comparable to those obtained by Test Method D2318.

1.2 Since this test method is empirical, strict adherence to all details of the procedure is necessary.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazards are given in Section 7, 6.2, and 6.3.

2. Referenced Documents

2.1 ASTM Standards:²

D70 Test Method for Density of Semi-Solid Bituminous Materials (Pycnometer Method)

D95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation

D329 Specification for Acetone

D850 Test Method for Distillation of Industrial Aromatic Hydrocarbons and Related Materials

D2318 Test Method for Quinoline-Insoluble (QI) Content of Tar and Pitch

D4296 Practice for Sampling Pitch

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke and Carbon Material.

Current edition approved May 1, 2014. Published May 2014. Originally approved in 1987. Last previous edition approved in 2013 as D4746 – 98 (2013). DOI: 10.1520/D4746-14E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E1 Specification for ASTM Liquid-in-Glass Thermometers

3. Summary of Test Method

3.1 The sample is digested in hot quinoline and filtered through a heated pressure filter. The insoluble material is washed with hot, fresh quinoline and with cold acetone, dried, and weighed.

4. Significance and Use

4.1 This test method is useful in evaluating and characterizing tar and pitch and as one element in establishing the uniformity of shipments and sources of supply.

5. Apparatus

5.1 *Pressure Filtration Vessel*—The pressure filtration vessel³ (see Fig. 1) is a stainless steel (304) jacketed block heated by steam or cooled with water, sealed by a lid, flat gasket, and clamp. The interior of the block is designed to accept a 3A2 Berlin porcelain filtration crucible (see 5.4). The crucible is sealed within the block by the use of three O-rings, a crucible sealing collar, and an adjustable plunger.

5.1.1 The seal is accomplished when the sealing lid is placed on top of the block and clamped. The adjustable plunger applies a force to the crucible sealing collar, which in turn pushes downward on the crucible and simultaneously compresses O-ring gaskets, forming a seal between surfaces of the crucible and the wall of the block. The filtration of material is accomplished by nitrogen (10 psig to 30 psig) introduced through the lid of the pressure filter. The filtrate exits from the drain tube at the bottom of the block. The filtrate is disposed into a Buchner flask, attached to drain tube by a No. 7 rubber stopper. A vacuum hose is attached to the Buchner flask and placed in a 100 mL beaker containing water to indicate the exit of nitrogen when the filtration is completed.

5.2 *Beaker*, 50 mL.

³ The sole source of supply of the pressure filtration vessel known to the committee at this time is Koppers Inc., 436 Seventh Ave., Pittsburgh, PA 15219-1800. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

*A Summary of Changes section appears at the end of this standard