



Designation: D5102/D5102M – 24

Standard Test Methods for Unconfined Compressive Strength of Compacted Soil-Lime Mixtures¹

This standard is issued under the fixed designation D5102/D5102M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers procedures for preparing, curing, and testing laboratory-compacted specimens of soil-lime and other lime-treated materials (**Note 1**) for determining unconfined compressive strength. Depending on the diameter to height ratio, two procedures for determining the unconfined compressive strength of compacted soil-lime mixtures have been developed for specimens prepared at the maximum unit weight and optimum water content, or for specimens prepared at other target unit weight and water content levels. Other applications are given in Section 5 on Significance and Use.

NOTE 1—Lime-based products other than commercial quicklime and hydrated lime are also used in the lime treatment of fine-grained cohesive soils. Lime kiln dust (LKD) is collected from the kiln exhaust gases by cyclone, electrostatic, or baghouse-type collection systems. Some lime producers hydrate various blends of LKD plus quicklime to produce a lime-based product.

1.2 Cored specimens of soil-lime should be tested in accordance with Test Methods **D2166/D2166M**.

1.3 Two alternative procedures are provided:

1.3.1 Procedure A describes procedures for preparing and testing compacted soil-lime specimens having height-to-diameter ratios between 2.00 and 2.50. This test method provides the standard measure of compressive strength.

1.3.2 Procedure B describes procedures for preparing and testing compacted soil-lime specimens using Test Methods **D698** compaction equipment and molds commonly available in most soil testing laboratories. Procedure B is considered to provide relative measures of individual specimens in a suite of test specimens rather than standard compressive strength values. Because of the lesser height-to-diameter ratio (1.15) of the cylinders, compressive strength determined by Procedure B will normally be greater than that by Procedure A.

1.3.3 Results of unconfined compressive strength tests using Procedure B should not be directly compared to those obtained using Procedure A.

¹ These test methods are under the jurisdiction of ASTM Committee **D18** on Soil and Rock and is the direct responsibility of Subcommittee **D18.15** on Stabilization With Admixtures.

Current edition approved Feb. 1, 2024. Published March 2024. Originally approved in 1996. Last previous edition approved in 2022 as D5102/D5102M – 22. DOI: 10.1520/D5102_D5102M-24.

1.4 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice **D6026**.

1.4.1 The method used to specify how data are collected, calculated, or recorded in this standard is not directly related to the accuracy to which the data can be applied in design or other uses, or both. How one applies the results obtained using this standard is beyond its scope.

1.5 Lime is not an effective stabilizing agent for all soils. Some soil components such as sulfates, phosphates, organics, etc. can adversely affect soil-lime reactions and may affect the test results using this method.

1.6 **Units**—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.6.1 The gravitational system of inch-pound units is used when dealing with inch-pound units. In this system, the pound (lbf) represents a unit of force (weight), while the unit for mass is slugs. The rationalized slug unit is not given, unless dynamic ($F = ma$) calculations are involved.

1.6.2 It is common practice in the engineering/construction profession to concurrently use pounds to represent both a unit of mass (lbm) and of force (lbf). This implicitly combines two separate systems of units; that is, the absolute system and the gravitational system. It is scientifically undesirable to combine the use of two separate sets of inch-pound units within a single standard. As stated, this standard includes the gravitational system of inch-pound units and does not use/present the slug unit for mass. However, the use of balances or scales recording pounds of mass (lbm) or recording density in lbm/ft³ shall not be regarded as non-conformance with this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. For specific precautionary statements, see Section 8.*

*A Summary of Changes section appears at the end of this standard