



Designation: D5321/D5321M – 20

Standard Test Method for Determining the Shear Strength of Soil-Geosynthetic and Geosynthetic-Geosynthetic Interfaces by Direct Shear¹

This standard is issued under the fixed designation D5321/D5321M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a procedure for determining the shear resistance of a geosynthetic against soil, or a geosynthetic against another geosynthetic, under a constant rate of deformation.

1.1.1 The test method is intended to indicate the performance of the selected specimen by attempting to model certain field conditions. Results obtained from this method may be limited in their applicability to the specific conditions considered in the testing.

1.2 The test method is applicable for all geosynthetics, with the exception of geosynthetic clay liners (GCLs), which are addressed in Test Method [D6243/D6243M](#).

1.3 The test method is not suited for the development of exact stress-strain relationships for the test specimen due to the nonuniform distribution of shearing forces and displacement.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee [D35](#) on Geosynthetics and is the direct responsibility of Subcommittee [D35.01](#) on Mechanical Properties.

Current edition approved Feb. 15, 2020. Published March 2020. Originally approved in 1992. Last previous edition approved in 2019 as D5321/D5321M – 19. DOI: 10.1520/D5321_D5321M-20.

2. Referenced Documents

2.1 *ASTM Standards*:²

[D653](#) Terminology Relating to Soil, Rock, and Contained Fluids

[D698](#) Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400 ft-lbf/ft³ (600 kN-m/m³))

[D1557](#) Test Methods for Laboratory Compaction Characteristics of Soil Using Modified Effort (56,000 ft-lbf/ft³ (2,700 kN-m/m³))

[D2435/D2435M](#) Test Methods for One-Dimensional Consolidation Properties of Soils Using Incremental Loading

[D2487](#) Practice for Classification of Soils for Engineering Purposes (Unified Soil Classification System)

[D3080/D3080M](#) Test Method for Direct Shear Test of Soils Under Consolidated Drained Conditions

[D3740](#) Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction

[D4354](#) Practice for Sampling of Geosynthetics and Rolled Erosion Control Products (RECPs) for Testing

[D4439](#) Terminology for Geosynthetics

[D6243/D6243M](#) Test Method for Determining the Internal and Interface Shear Strength of Geosynthetic Clay Liner by the Direct Shear Method

[D7005/D7005M](#) Test Method for Determining the Bond Strength (Ply Adhesion) of Geocomposites

[D7466/D7466M](#) Test Method for Measuring Asperity Height of Textured Geomembranes

3. Terminology

3.1 *Definitions*:

3.1.1 For definitions of terms relating to soil and rock, refer to Terminology [D653](#). For definitions of terms relating to geosynthetics, refer to Terminology [D4439](#).

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *adhesion, c_a , n* —the y-intercept of the Mohr-Coulomb strength envelope.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.