



Designation: D5458 – 95 (Reapproved 2020)

Standard Test Method for Peel Cling of Stretch Wrap Film¹

This standard is issued under the fixed designation D5458; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method measures cling between two layers of film, in both a stretched and unstretched condition.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D996 Terminology of Packaging and Distribution Environments

D1898 Practice for Sampling of Plastics (Withdrawn 1998)³

D4332 Practice for Conditioning Containers, Packages, or Packaging Components for Testing

E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

¹ This test method is under the jurisdiction of ASTM Committee D10 on Packaging and is the direct responsibility of Subcommittee D10.25 on Palletizing and Unitizing of Loads.

Current edition approved Nov. 1, 2020. Published November 2020. Originally approved in 1994. Last previous edition approved in 2012 as D5458 – 95 (2012). DOI: 10.1520/D5458-95R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3. Terminology

3.1 *Definitions*—General definitions for packaging and distribution environments are found in Terminology D996.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *cling*—the property of a material's ability to adhere to itself.

3.2.2 *stretch wrap material*—a material used for overwrapping which, when applied under tension, elongates, and through elastic recovery, conforms to the item(s) packaged.

4. Summary of Test Method

4.1 This test method is a peel cling procedure. A 1 in. (25 mm) wide film strip is adhered to a flat film attached to an inclined surface. The force required to remove the film strip from the flat film is measured.

5. Significance and Use

5.1 Cling is of critical importance in maintaining a tight wrap after a load is stretch wrapped.

6. Equipment and Preparation

6.1 *Apparatus*—A universal testing machine with a constant rate of grip separation equipped, as follows:

6.1.1 One lightweight jaw equipped with 1 by 1.5 in. (25 by 38 mm) flat rubber-faced grips,

6.1.2 Cling attachment (see Figs. 1-5),

6.1.3 Cling clamp (see Fig. 6),

6.1.4 Load cell, 500-g load capacity,

6.1.5 If using pneumatic grips, air supply, 60 to 70 psi with appropriate filter,

6.1.6 Sample template, picture-frame style with inside dimensions of 5 by 20 in. (125 by 500 mm),

6.1.7 Precision sample cutter, 1 ± 0.001 in. (25.4 ± 0.03 mm) width, with precision of 1 ± 0.001 in. (25.4 ± 0.03 mm),⁴

6.1.8 Single-edged safety razor blade,

6.1.9 Synthetic bristle paint brush, 2 in. (50 mm) wide,

6.1.10 Ruler, 12 in. (approximately 300 mm),

6.1.11 Separation paper, 8.5 by 12 in. (approximately 125 by 280 mm) bond,

⁴ JDC-1-10 Cutter is available from Thwing-Albert Instrument Co., 10960 Dutton Rd., Philadelphia, PA 19154 or other manufacturers.