



Designation: D5507 – 21a

Standard Test Method for Determination of Trace Organic Impurities in Monomer Grade Vinyl Chloride by Capillary Column/Multidimensional Gas Chromatography¹

This standard is issued under the fixed designation D5507; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This is a general-purpose capillary-based test method for the determination of trace level impurities in high-purity vinyl chloride. This test method uses serially coupled capillary PLOT columns in conjunction with the multidimensional techniques of column switching and cryogenic trapping to permit the complete separation of the 11 key vinyl chloride impurities in a single 25-min run.

NOTE 1—There is no known ISO equivalent to this standard.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific hazards statements are given in Section 8.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D883 Terminology Relating to Plastics

D1600 Terminology for Abbreviated Terms Relating to Plastics

E456 Terminology Relating to Quality and Statistics

E2935 Practice for Conducting Equivalence Tests for Comparing Testing Processes

F307 Practice for Sampling Pressurized Gas for Gas Analysis

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.70 on Analytical Methods.

Current edition approved May 1, 2021. Published May 2021. Originally approved in 1994. Last previous edition approved in 2021 as D5507 – 21. DOI: 10.1520/D5507-21A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *Definitions*—For definitions of terms in this test method relating to plastics, refer to Terminology D883. For abbreviations used in this test method, refer to Terminology D1600. For definitions of terms that appear in this test method relating to quality and statistics, refer to Terminology E456.

4. Summary of Test Method

4.1 The liquid vinyl chloride sample or calibration standard is injected either directly using a high-pressure liquid sampling valve or alternately as an expanded gas. An appropriate volume of the liquid or gas sample is injected to enable the required detection limits to be achieved. A preliminary GC separation is achieved on a 6-m pre-column, the purpose of which is to remove the bulk of the vinyl chloride peak from the trace peaks of interest. Two heart-cut transfers are made from this pre-column separation, which sends selected portions to a second column for additional separation. These two cuts incorporate 10 of the 11 trace impurities of interest, but they exclude 1,2 ethylene dichloride and the bulk of the vinyl chloride peak. The 1,2 EDC peak is eluted from the 6-m pre-column and detected at the first FID after the two cuts are made.

4.2 The components eluting to the two FID detectors are identified and quantitated by comparing their retention times and area counts to those obtained previously from a calibration standard run under identical conditions.

5. Significance and Use

5.1 The multidimensional approach permits all of the trace impurities to be well separated from the main vinyl chloride peak, thereby improving quantitative accuracy over established packed column methods.

5.2 The minimum detection limit (MDL) for all components of interest has been shown to be well below 500 ppb for this test method.

6. Apparatus

6.1 *Instrumentation:*

6.1.1 *Capillary Column/Multidimensional Gas Chromatograph*, equipped as follows:

*A Summary of Changes section appears at the end of this standard